



## ISTITUTO NAZIONALE DI RICERCA METROLOGICA Repository Istituzionale

Investigating the provenance of Italian archaeological obsidian tools based on their magnetic properties

This is the author's accepted version of the contribution published as:

*Original*

Investigating the provenance of Italian archaeological obsidian tools based on their magnetic properties / Ferrara, E.; Beatrice, C.. - In: ARCHAEOLOGICAL AND ANTHROPOLOGICAL SCIENCES. - ISSN 1866-9565. - (2019). [10.1007/s12520-018-0757-9]

*Availability:*

This version is available at: 11696/59707 since: 2023-06-20T14:26:05Z

*Publisher:*

Springer

*Published*

DOI:10.1007/s12520-018-0757-9

*Terms of use:*

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

*Publisher copyright*  
SPRINGER NATURE

This version of the article has been accepted for publication, after peer review (when applicable) and is subject to Springer Nature's AM terms of use, but is not the Version of Record and does not reflect post-acceptance improvements, or any corrections.

(Article begins on next page)

# Archaeological and Anthropological Sciences

## Investigating the provenance of Italian archaeological obsidian tools based on their magnetic properties

--Manuscript Draft--

<b>Manuscript Number:</b>	AASC-D-18-00180R1
<b>Full Title:</b>	Investigating the provenance of Italian archaeological obsidian tools based on their magnetic properties
<b>Article Type:</b>	Original Paper
<b>Corresponding Author:</b>	Enzo FERRARA Istituto Nazionale di Ricerca Metrologica Torino, Piemonte ITALY
<b>Corresponding Author Secondary Information:</b>	
<b>Corresponding Author's Institution:</b>	Istituto Nazionale di Ricerca Metrologica
<b>Corresponding Author's Secondary Institution:</b>	
<b>First Author:</b>	Enzo FERRARA
<b>First Author Secondary Information:</b>	
<b>Order of Authors:</b>	Enzo FERRARA Evdokia Tema Elena Zanella Cinzia Beatrice Francesca Miola Elena Pavesio Andrea Perino
<b>Order of Authors Secondary Information:</b>	
<b>Funding Information:</b>	
<b>Abstract:</b>	<p>Reconstructing the distribution of ancient obsidian tools is one of the few ways to trace ancient trade routes during the Neolithic. The use of magnetic properties for obsidian provenance studies has already been applied as a useful inexpensive and non-destructive tool. It is mainly based on the variation of the type, concentration, and grain size of the magnetic particles within the vitreous matrix coming from different sources. In this study, we present the results of a rock magnetic investigation carried out on archaeological obsidian tools collected from six Neolithic sites situated in Northern Italy (Castello d'Annone, Brignano Frascata, Cascina Chiappona, Casalnoceto, Garbagna, and Parma). A total of 57 archaeological samples were analyzed by measuring several magnetic parameters such as: low field and anhysteretic susceptibility, saturation isothermal remanent magnetization at room and liquid nitrogen temperature, remanence and saturation magnetization from hysteresis cycles, and anisotropy of low field susceptibility. The obtained results were compared with the magnetic properties of geological samples from five Mediterranean islands (Lipari, Sardinia, Palmarola, Pantelleria, and Melos). Cluster analysis was applied to the whole set of parameters, allowing the correlation of the pertinent group of artefacts and geological obsidians. Such analysis shows that most of the studied archaeological tools come from Lipari, with few exceptions consisting of samples coming from Pantelleria and Sardinia. Our results are in good agreement with other studies based on chemical analyses that also show that Lipari is the most common Neolithic obsidian source in Northern Italy, despite its longer distance in respect to other obsidian sources.</p>
<b>Response to Reviewers:</b>	Torino, November 9th 2018

# Investigating the provenance of Italian archaeological obsidian tools based on their magnetic properties

Enzo Ferrara<sup>1,\*</sup>, Evdokia Tema<sup>2,3</sup>, Elena Zanella<sup>2,3</sup>, Cinzia Beatrice<sup>1</sup>,

Francesca Miola<sup>1</sup>, Elena Pavesio<sup>1</sup>, Andrea Perino<sup>1</sup>

<sup>1</sup>*Istituto Nazionale di Ricerca Metrologica, Strada delle Cacce 91, 10135 Torino, Italy*

<sup>2</sup>*Dipartimento di Scienze della Terra, Università degli studi di Torino, via Valperga Caluso 35,  
10125 Torino, Italy*

<sup>3</sup>*CIMaN-ALP Palaeomagnetic Laboratory, via G. U. Luigi Massa 6, 12016 Peveragno, Italy*

\*Corresponding author: Istituto Nazionale di Ricerca Metrologica, Strada delle Cacce 91, 10135  
Torino, Italy. Tel.: +39 011 3919837, E-mail address: [e.ferrara@inrim.it](mailto:e.ferrara@inrim.it)

## Abstract

Reconstructing the distribution of ancient obsidian tools is one of the few ways to trace ancient trade routes during the Neolithic. The use of magnetic properties for obsidian provenance studies has already been applied as a useful inexpensive and non-destructive tool. It is mainly based on the variation of the type, concentration, and grain size of the magnetic particles within the vitreous matrix coming from different sources. In this study, we present the results of a rock magnetic investigation carried out on archaeological obsidian tools collected from six Neolithic sites situated in Northern Italy (Castello d'Annone, Brignano Frascata, Cascina Chiappona, Casalnoceto, Garbagna, and Parma). A total of 57 archaeological samples were analyzed by measuring several magnetic

1 parameters such as: low field and anhysteretic susceptibility, saturation isothermal remanent  
2 magnetization at room and liquid nitrogen temperature, remanence and saturation magnetization from  
3 hysteresis cycles, and anisotropy of low field susceptibility. The obtained results were compared with  
4 the magnetic properties of geological samples from five Mediterranean islands (Lipari, Sardinia,  
5 Palmarola, Pantelleria, and Melos). Cluster analysis was applied to the whole set of parameters,  
6 allowing the correlation of the pertinent group of artefacts and geological obsidians. Such analysis  
7 shows that most of the studied archaeological tools come from Lipari, with few exceptions consisting  
8 of samples coming from Pantelleria and Sardinia. Our results are in good agreement with other studies  
9 based on chemical analyses that also show that Lipari is the most common Neolithic obsidian source  
10 in Northern Italy, despite its longer distance in respect to other obsidian sources.  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26

27 **Keywords:** Obsidian; Provenance; Magnetic properties; Neolithic; Italy  
28  
29  
30  
31  
32

## 33 **1. Introduction**

34  
35  
36 In Central Europe, obsidian tools were abundantly used as cutting utensils during the  
37 prehistoric period, before the employment of metallic alloys, and they remain the ancient trading  
38 artifacts most used to reconstruct trade routes in the Neolithic (Cann and Renfrew 1964; Renfrew et  
39 al. 1965; Freund 2018). In the Mediterranean area, a few obsidian sources are available, located at  
40 the volcanic islands of Lipari, Palmarola, Pantelleria and Sardinia in Italy, and at Melos and Gyalis in  
41 Greece (Fig. 1). Obsidians from these sources have distinctive chemical compositions, which have  
42 been considered as a fingerprint and used for provenance investigations of Neolithic artefacts found  
43 in the archaeological sites of Central Europe (Scorzelli et al. 2001; Poupeau et al. 2007; Weaver et  
44 al. 2009).  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

Apart from differences in the chemical composition of obsidians, variations of the size, distribution, and structure of the ferrous grains in the amorphous matrix may occur in both outcrop and sample scale, depending on the geochemistry of the lava and the conditions under which the volcanic eruption and subsequent cooling of the magma took place. Such important variants may be detected as changes in the magnetic properties of obsidians from different geological sources. Magnetic measurements can therefore offer an alternative approach of non-destructive and cheap laboratory methods to investigate obsidian provenance, in comparison with the conventional trace element analysis or to the examination of physical-chemical properties such as the thickness of the hydrated layer (Liritzis and Laskaris, 2011), and the extent of geochronological fission tracks (Bigazzi et al. 1990).

Several decades ago, McDougall et al. (1983) first examined the potential of magnetic measurements to investigate the provenance of obsidian artifacts by studying samples from Mediterranean and Near Eastern sources. Since then, several other studies focused on the use of magnetic properties in sourcing archaeological obsidians, often introducing new parameters to obtain clearer provenance correlations and/or integrating them to other analyses e.g. geochemical measurements, <sup>57</sup>Fe Mossbauer spectroscopy, and X-ray fluorescence (XRF) (Urrutia Fucugauchi 1999; Vasquez et al. 2001; Tykot 2002; Stewart et al. 2003; Zanella et al. 2012; Frahm et al. 2014; Mameli et al. 2016). However, magnetic approaches have often shown variable success, probably because of the complex magnetic and microstructural features of the obsidians, which can result in unclear source determination (Vasquez et al. 2001). Frahm and Feinberg (2013) investigated a large number of geological and archaeological obsidians, observing important magnetic variability across an individual flow. They thus suggested the use of magnetic properties to identify quarrying locations within a flow, rather than using them to source artifacts to an obsidian flow. Frahm et al. (2014) further explored the potential of magnetic properties in sourcing obsidians from Armenia, concluding that the measurement of few basic magnetic parameters could contribute to distinguish geochemically identical obsidians from different eruptive centers.

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

In this study, we further investigate the use of magnetic analyses for archaeological obsidian sourcing by presenting new magnetic data from obsidian bladelets and nodules collected from six Neolithic sites (Castello d'Annone, Brignano Frascata, Cascina Chiappona, Casalnoceto, Garbagna, and Parma) situated in Northern Italy. The new data are compared with the magnetic properties previously determined (Zanella et al., 2012) on geological samples from the main Central Mediterranean obsidian sources (Lipari, Sardinia, Palmarola, Sardinia Monte Arci, Pantelleria, and Melos). In addition to the magnetic parameters proposed in Zanella et al. (2012), we consider here also the anisotropy of low field susceptibility,  $P$ , as a useful additional indicator to discriminate samples from the sources of Lipari and Sardinia SA, both characterized by large content of superparamagnetic grains and thus undistinguishable using other magnetic parameters. Cluster analysis is finally applied on the resulting dataset, as a suitable representation of the different groups used to identify and correlate geological and archaeological obsidians.

## 2. Material and methods

### 2.1 Archaeological samples

A collection of 57 archaeological obsidians has been studied. The samples come from six archaeological sites found in Northern Italy, five of them situated in Piedmont and one at Parma (Fig. 1). Specifically, the samples from the prehistoric settlements in Piedmont are: 22 samples from Castello d'Annone (CDA), 1 sample from Garbagna (Ossi 6), 3 samples from Cascina Chiappona (Ossi 7-9), 3 samples from Brignano Frascata (Ossi 10-12), and 8 samples from Casalnoceto (Ossi 13-20). Almost all samples are obsidian bladelets, with only exception two samples from Castello d'Annone (CDA I and II), two samples from Casalnoceto (Ossi 19 and 20) and one sample from Brignano Frascata (Ossi 12) that are obsidian nodules.

The obsidians from Piedmont were collected during excavations in the 80's and 90's and they were catalogued and stored at the Museum of Antiquity of Torino (Venturino Gambari 2004). Even

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

though from some sites the number of available archaeological tools is very limited (e.g. only one sample from the Garbagna site), the Piedmont sites of Garbagna, Cascina Chiappona, Brignano Frascata and Casalnoceto are located in the same area (Fig. 1), and can therefore be considered altogether for investigating the provenance of obsidian tools in this area of Northern Italy. The obsidians from Parma consist of 20 samples (GUI) and come from a settlement found in the urban habitat of the city, in the modern via Guidorossi (Bernabò Brea et al. 1988; Quero 2014). According to archaeological evidence, all the studied sites were inhabited in the mid-late Neolithic period (Venturino Gambari 1988, 1993), even though detailed information on their precise dating is not available.

The dimensions of the studied archaeological bladelets and nodules are generally small, ranging from 3-4 mm to 20 mm (Fig. 2). Their masses vary from 0.08 g to 4 g. With the only exception of a larger bladelet from Castello d'Annone (CDA I), all samples were sufficiently small to be placed in plastic sample holders that made possible the performance of the magnetic measurements without cutting or harming them, confirming the non-destructive character of such analyses.

## 2.2 Magnetic measurements

The magnetic granulometry of the obsidian artefacts was investigated by the measurement of: low field susceptibility ( $\chi$ ), anhysteretic susceptibility ( $\chi_a$ ), saturation of isothermal remanent magnetization at room temperature (SIRM<sub>293</sub>) and in liquid nitrogen (SIRM<sub>77</sub>), and anisotropy of magnetic susceptibility (P). Furthermore, the susceptibility ratio ( $Q_a$ ), the SIRM<sub>77</sub>/SIRM<sub>293</sub> ratio ( $S_T$ ), and the ratio of remanence and saturation magnetization ( $M_R/M_S$ ), as evidenced through hysteresis cycles, were calculated.

### 2.2.1 Low-field and anhysteretic susceptibility

1  
2 The low field susceptibility was first measured on all samples using a KLY-3 Kappabridge  
3 (Agico). An accurate evaluation and subtraction of the diamagnetic contribution due to the plastic  
4 container and sample holder was applied, particularly for samples with mass lower than 0.2 g (in such  
5 very small samples the diamagnetic contribution of the plastic holder may be very important). In  
6 order to avoid the directional bias due to the large magnetic anisotropy of obsidians (Lanci and  
7 Zanella 2016), the anisotropy of the magnetic susceptibility (AMS) was also measured and the AMS  
8 anisotropy degree,  $P = K1/K3$ , defined as the ratio of the maximum susceptibility axis (K1) and the  
9 minimum susceptibility axis (K3), was calculated (Tarling and Hrouda 1993).  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21

22 The anisotropy of the anhysteretic remanent magnetization ( $J_{ARM}$ ) was measured using a D-  
23 2000 ASC equipment and a JR-6 spinner magnetometer. Each sample was initially tumbling  
24 demagnetized with an alternating field (AF) of 200 mT to erase as much as possible of the original  
25 hard natural remanent magnetization (NRM) component. Then the ARM was evaluated imposing a  
26 steady field  $H_{DC} = 100 \mu T$  (i.e. within the Rayleigh region) in the presence of an AF field of 100 mT.  
27 Following, the remanent magnetization  $J_{ARM}$  was measured. The procedure was repeated in six  
28 different orientations with respect to the applied direct field ( $H_{DC}$ ) and in two opposite senses for each  
29 position to cancel out any unwanted contribution by unerased NRM (12 positions in total). Finally,  
30 the anhysteretic susceptibility,  $\chi_a = J_{ARM}/H$ , was calculated. The ratio  $Q_a$  is then defined as  $Q_a = \chi_a / \chi$   
31 (Zanella et al. 2012).  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50

### 51 2.2.2 Isothermal Remanent Magnetization

52 Stepwise acquisition of the isothermal remanent magnetization (IRM) was measured up to 2T  
53 IRM curves were obtained at two temperatures: 293 K and 77 K. Each sample was blocked with  
54 plastiline in a small plastic open box, and a stepwise increasing direct field was applied with an ASC  
55 pulse magnetizer. After each step, the IRM was measured with a 2G Enterprises cryogenic  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65



magnetometer. For the acquisition of IRM at low temperature, the same field sequence was followed but before each step the open box container with the sample was bathed in liquid nitrogen and let cool down until 77 K. The IRM saturation values obtained at 293 K ( $SIRM_{293}$ ) and at 77 K ( $SIRM_{77}$ ) were then used to calculate the  $S_T$  ratio, defined as  $S_T = SIRM_{77}/SIRM_{293}$ .

### 2.2.3 Hysteresis loops and magnetization values

Remanence (MR) and saturation magnetization (MS) at room temperature were obtained from the hysteresis cycles whose shape variation with temperature can provide information on the magnetic granulometry (Zanella et al. 2012). Each archaeological sample was measured with a Vibrating Sample Magnetometer (VSM – Lake Shore 7400) or, for larger obsidians, with a Cryogenic Magnetometer (Oxford Instrument Cryomagnet), with a maximum applied field  $B = \pm 1$  T. Samples were tightly clamped on the holder using diamagnetic tape. Such measurements were furthermore repeated at two temperatures, 293 K and 77 K, for all the samples, in the latter case maintaining obsidians in liquid nitrogen during the analysis.  $M_S$  values were interpolated through subtraction from the loop of the linear paramagnetic contribute emergent at high magnetizing fields.

### 2.2.4 Cluster Analysis

As former studies have shown, overlaps may occur in the confidence intervals of the various magnetic parameters obtained from the different obsidian sources. To overcome this limitation, multivariate analysis was applied using Cluster 3.0 software. The results were graphically represented using Java Treeview, an open-source software platform that can handle very large datasets allowing the visualization and comparison of the data.

## 3. Results

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

The results of the magnetic parameters measured for all the archaeological obsidian samples are analytically reported in Table 1. These parameters are similar to those used by Zanella et al. (2012) on geological samples from Lipari (Canneto, Diana, and Piano Conte), Palmarola, Pantelleria, Sardinia (SA, SB1, SB2, and SC), and Melos. However, to allow the direct comparison between the archaeological and geological samples, avoiding discrepancies due to possible different ways of calculating the various parameters, the previously published magnetic results from the Mediterranean geological obsidians (Zanella et al. 2012) are reported in Table 2, using the same calculations, parameters, ratios and format as those used for the archaeological samples in this study (Table 1).

The IRM curves obtained for representative archaeological samples (GUI 38, CDA 04, CDA 08) at 293 K and 77 K are plotted in Fig. 3, together with the same plots from typical geological samples from Lipari, Sardinia (SB) and Melos. Such curves indicate that most of the archaeological obsidians show large changes in IRM while passing from room temperature to liquid nitrogen temperature, resembling the behavior shown by the geological obsidians from Lipari (Fig. 3). These data are also confirmed by the hysteresis loops obtained at 293 K and 77 K (Fig. 4). In almost all cases the loops obtained at 77 K have larger magnetic moment than those obtained at 293 K, while an important paramagnetic contribution is clearly seen, with linear increase of the magnetic moment at high fields, accompanied by a large increase of the coercive force (e.g. Fig. 4 g, j, k). These samples have a similar behavior to that obtained from geological samples from Lipari (Fig. 4a), which contain a large amount of superparamagnetic (SP) grains whose magnetization is not stable at room temperature (Zanella et al. 2012). In other cases, the increase of magnetization and coercive field when measured at low temperature (77K) is not as large as in the previous samples (e.g. Fig. 4 f, i). Finally, there are also few samples showing a very important change of magnetic moment between room and liquid nitrogen temperature, characterized by an almost linear behavior of the magnetic moment versus field, with a faint ferrimagnetic content and a large paramagnetic contribution (e.g. Fig. 4 e, h).

1 The anhysteretic and low-field magnetic susceptibilities measured from both archaeological  
2 and geological samples have been plotted in a King plot (King et al. 1982) in Fig. 5. It can be noticed  
3 that most of the archaeological samples coincide with low values in the  $\chi_a$  vs.  $\chi$  plot, similar to the  
4 geological samples from Lipari, with the exception of some samples mainly coming from Piedmont.  
5  
6 However, as already pointed out by Zanella et al. (2012), the King plot does not succeed to entirely  
7 discriminate the different geological sources, particularly between samples from Lipari and Sardinia  
8 SA and samples from Palmarola and Melos, which are generally characterized by similar  $\chi_a$  vs.  $\chi$   
9 values. For this reason, the ratio  $Q_a = \chi_a / \chi$  and the ratio  $S_T = \text{SIRM}_{77} / \text{SIRM}_{293}$ , proposed by Zanella  
10 et al. (2012), have been calculated and plotted in Fig. 6 introducing also the anisotropy of  
11 susceptibility P, graphically represented as three-dimensional plots (Fig. 6). These plots seem to be  
12 more effective in separating the different obsidian groups, in particular the geological obsidians from  
13 Sardinia SA and those from Lipari (Fig. 6 a), confirming that the use of the parameter P can be  
14 essential for separating the different sources. The three-dimensional representations are also effective  
15 to distinguish the provenance of most archaeological samples. The samples from Parma clearly group  
16 with the geological samples from Lipari (Fig. 6 a) as most of the samples from Piedmont, which also  
17 distribute preferentially around the geological obsidians from Lipari (Fig. 6b), with some exceptions  
18 mainly for the samples from Casalnoceto and Castello d'Annone that show scattered values, probably  
19 indicating various possible sources (Fig. 6 b, c).  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42

43 Finally, the normalized quantities  $\chi$ ,  $\chi_a$ ,  $Q_a$ ,  $\text{SIRM}_{293}$ ,  $\text{SIRM}_{77}$ ,  $S_T$ ,  $M_R/M_S$ , and P were  
44 elaborated using cluster analysis and the obtained results are plotted in the form of dendrograms (Fig.  
45 7). The multivariate analysis has been conducted on the normalized magnetic parameters, so it is not  
46 possible to quantify definitely the distances among different obsidian groups. However, such analysis  
47 can offer a qualitative interpretation based on the relative distances among the groups, which can be  
48 appreciated through the ordinate value reported in the graphs, or the height of the line connecting the  
49 different clusters. Compound clusters are in fact formed by joining individual obsidians having the  
50 shorter distance in the multivariate space, with the join point referred to as a node. Numerical  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

1 correlations among different objects and groups in the dendrogram are thus proportional to their  
2 Euclidean distance that corresponds to the value of the vertical axis and refers to the measure between  
3 adjacent individual objects or compound clusters. As we move up in the dendrogram, the compound  
4 clusters get bigger and the distance between adjacent clusters increases. Indeed, the cluster analysis  
5 applied on the geological samples shows that all the geological sources, including Sardinia SA,  
6 clearly separate (Fig. 7 a). Samples from Sardinia SB1 and SC, having lower SP and larger single  
7 domain (SD) grains, differentiate neatly from all the other sources and constitute a separate group.  
8 Samples from Pantelleria also group separately as well as samples from Lipari that are well grouped  
9 and form a distinct cluster.

10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22 The same dendrograms have been used to identify the provenance of the archaeological  
23 samples studied here, based on their magnetic affinity to the geological groups. Although introducing  
24 the archaeological obsidians in the multivariate analysis slightly modifies the relative distances of the  
25 dendrograms, yet it seems that such analysis can successfully separate the different groups. For the  
26 samples from Parma, the cluster analysis (Fig. 7b) clearly associates all of them to Lipari. For the  
27 sites of Garbagna, Casalnoceto, and Cascina Chiappona the dendrogram confirms Lipari as a source  
28 of 7 samples (Fig. 7c). From Casalnoceto, two samples (Ossi 14 and Ossi 20) seem to group with  
29 samples from Palmarola, as already indicated by the hysteresis loops and the King Plot (Fig. 5). Few  
30 other samples from Piedmont are grouped with samples from Sardinia SA, mainly due to their high  
31 values of P and  $Q_a$ . All samples from Brignano Frascata are also clustered close to Sardinia geological  
32 obsidians (Fig. 7c). Among the 22 obsidians from Castello d'Annone, 9 samples group directly with  
33 Lipari and 11 have Palmarola as the only possible alternative to Lipari; CDA17 is probably an outlier,  
34 although it groups with Sardinia SB1 but at a large distance (Fig. 7d).

#### 57 **4. Discussion and conclusions**

58  
59  
60  
61  
62  
63  
64  
65

1 Even though obsidian is a complex volcanic material, which can contain different magnetic  
2 phases that may influence its magnetic properties, depending on the concentration, shape and grain-  
3 size of the ferromagnetic grains, yet this study shows that the investigation of several magnetic  
4 parameters and their combinations can be a useful tool for obsidian sourcing studies. Criticisms  
5 persists on the possibility to apply magnetic granulometry for obsidian provenance in regions where  
6 outcrops of volcanic glasses show inhomogeneous magnetic features (Frahm et al. 2012; 2014; 2016;  
7 Rochette et al. 2015); nevertheless this technique is available in addition to compositional and  
8 geochronological analysis for matching artifacts to a specific obsidian source among Mediterranean  
9 outcrops. For this purpose, we suggest the use of seven simple and easily measured magnetic  
10 parameters (low field and anhysteretic susceptibilities, saturation isothermal remanent magnetizations  
11 at room, 293 K, and liquid nitrogen, 77 K, temperature, saturation and remanent magnetizations, and  
12 anisotropy of low field susceptibility), as a reference dataset for comparison between archaeological  
13 and geological obsidian magnetic behavior. In respect to the previously proposed parameters, we  
14 introduce here the use of  $P$  that seems to be effective on distinguishing obsidians with similar  $Q_a$  and  
15  $S_T$  values.

16 We have applied this approach to obsidian archaeological samples from six Neolithic sites in  
17 Northern Italy, comparing them with the magnetic properties of geological obsidians from the five  
18 major volcanic islands of the Mediterranean (Lipari, Sardinia, Palmarola, Pantelleria, and Melos).  
19 Our results show that the combined use of the King plot and  $Q_a$  vs.  $S_T$  plots, introducing also the  
20 degree of anisotropy,  $P$ , in three-dimensional representations, can effectively discriminate the origin  
21 of the archaeological obsidian tools. The applied multivariate analysis on the dataset, based on  
22 combined parameters as vectors in a multidimensional space, further contributes to provenance  
23 studies allowing the correlation with the volcanic sources when geological and archaeological  
24 samples fall in the same cluster.

25 According to our results, most of the archaeological obsidians from Northern Italy  
26 investigated in this study come from Lipari, with some other sources being also present. Indeed,  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

1 cluster analysis shows that all the archaeological samples from Parma are well grouped with the  
2 geological samples from Lipari and most of the samples from Casalnoceto and Cascina Chiappona  
3  
4 also gather with Lipari geological obsidians. Samples from Castello d'Annone show a more varied  
5  
6 origin with some samples coming from Lipari and other clustering with geological samples from  
7  
8 Palmarola and Pantelleria. All three studied samples from Brignano Frascata seem to come from  
9  
10 Sardinia. We haven't observed any systematic correlation between the provenance of the obsidians  
11  
12 and their use (e.g. bladelets and nodules). That's probably because most of the investigated samples  
13  
14 were bladelets and only five nodules were included in our archaeological obsidian collection, so that  
15  
16 it is not possible to drive clear conclusions on such a possible correlation.  
17  
18  
19  
20  
21

22 The results obtained here are in good agreement with other studies investigating the  
23  
24 distribution of archaeological obsidians in Northern Italy based on chemical analysis. Even though  
25  
26 finds of obsidians are comparatively rare in Northern Italy, early provenance studies have identified  
27  
28 obsidians from more than one source, mainly coming from Sardinia and Lipari, with more sites shown  
29  
30 to use Liparian obsidian rather than Sardinian one (Thorpe et al. 1979). Tykot (1996) reports that at  
31  
32 the Italian Middle Neolithic site of Gaione-Parma, obsidian from Sardinia, Palmarola and Lipari is  
33  
34 present, with a strong tendency towards blades being of Lipari obsidian and cores and trim of  
35  
36 Sardinian obsidian. Analyses from several Neolithic stratigraphic contexts from the archaeological  
37  
38 site of Arene Candite-Savona show that lithic assemblage from Early Neolithic comes equally from  
39  
40 Sardinia and Palmarola. However, in the Middle Neolithic, obsidian from Lipari replaces much of  
41  
42 the Sardinian SA and SB contribution while by the Late Neolithic nearly all obsidian artefacts are  
43  
44 finished blades of obsidian from Lipari (Ammerman and Polglase 1998; Costa 2007). According to  
45  
46 these authors, Lipari, notwithstanding its greater distance in comparison with Sardinia and Palmarola,  
47  
48 come to play an ever-increasing role in the exchange of obsidian in Northern Italy, probably because  
49  
50 of its high quality and its circulation as a prestige item in later Neolithic times, characterized by  
51  
52 greater demand. Our results further support such hypothesis, confirming Lipari as the main obsidian  
53  
54 source in Northern Italy. They also confirm that most of the studied archaeological sites belong to the  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

1  
2 Middle – Late Neolithic, while for the sites where various obsidian sources were identified, an older  
3  
4  
5  
6  
7 age cannot be excluded.

## 8 **Acknowledgement**

9  
10  
11 Marica Venturino (Soprintendenza per i Beni Archeologici del Piemonte e del Museo Antichità  
12  
13 Egizie) and Maria Bernabò Brea (Soprintendenza Archeologica dell'Emilia Romagna and Museo  
14  
15 Archeologico Nazionale di Parma) are warmly acknowledged for providing the archaeological  
16  
17 obsidian samples and for their precious collaboration and discussion. The Editor and two anonymous  
18  
19 reviewers are also acknowledged for their useful and constructive comments.  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

## References

1  
2 Ammerman A.G, Polglase C. (1998). Obsidian at Neolithic sites in Northern Italy. *Preistoria Alpina*,  
3  
4 34, 291-296.  
5  
6

7  
8  
9  
10 Bernabò Brea M., Ghiretti A., Polglase C., Visconti V. (1988). I siti neolitici lungo il torrente Cinghio  
11  
12 (Parma). *Preistoria Alpina – Museo Tridentino di Scienze Naturali*, 24, 103-164.  
13  
14  
15

16  
17  
18  
19 Bigazzi G., Marton P., Norelli P., Rozložnik L. (1990). Fission track dating of Carpathian obsidians  
20  
21 and provenance identification. *Nuclear Tracks and Radiation Measurements* 17(3), 391-396.  
22  
23  
24

25  
26  
27  
28 Cann J. R., Renfrew C. (1964). The Characterization of Obsidian and Its Application to the  
29  
30 Mediterranean. Region. *Proc. Prehistoric Soc.* (30), 111–133.  
31  
32  
33

34  
35  
36  
37 Costa L. J. (2007). *L'obsidienne. Un témoignage d'échanges en Méditerranée préhistorique*. Editions  
38  
39 Errance, Paris.  
40  
41

42  
43 Frahm E., Feinberg J. M. (2013). From flow to quarry: magnetic properties of obsidian and changing  
44  
45 the scale of archaeological sourcing. *Journal of Archaeological Science*, 40 (10), 3706–3721.  
46  
47 <http://dx.doi.org/10.1016/j.jas.2013.04.029>  
48  
49  
50

51  
52  
53  
54 Frahm E., Feinberg J. M., Schmidt-Magee B., Wilkinson K., Gasparyan B., Yeritsyan B., Karapetian  
55  
56 S., Meliksetian K., Muth M. J., Adler D. S. (2014). Sourcing Geochemically Identical Obsidian:  
57  
58 Multiscalar Magnetic Variations in the Gutansar Volcanic Complex and Implications for Palaeolithic  
59  
60  
61  
62  
63  
64  
65



<http://dx.doi.org/10.1016/j.jas.2014.04.015>

Frahm E., Feinberg J. M., Schmidt-Magee B.A., Wilkinson K. N., Gasparyan B., Yeritsyan B., Adler D.S. (2016). Middle Palaeolithic toolstone procurement behaviors at Lusakert Cave 1, Hrazdan valley, Armenia. *Journal of Human Evolution*, 91, 73-92.

Freund K.P. (2018). A long-term perspective on the exploitation of Lipari obsidian in central Mediterranean prehistory. *Quaternary International* 468, 109-120.

King J., Banerjee S. K., Marvin J., Ozdemir Ö. (1982). A comparison of different magnetic methods for determining the relative grain size of magnetite in natural materials: Some results from lake sediments, *Earth Planet. Sci. Lett.*, 59, 404–419. Doi:10.1016/0012-821X(82)90142-X

Lanci L., Zanella E. (2016). The anisotropy of magnetic susceptibility of uniaxial superparamagnetic particles: Consequences for its interpretation in magnetite and maghemite bearing rocks *Journal of Geophysical Research*, 121 (1), pp. 27–37. Doi:10.1002/2015JB012255

Liritzis I., Laskaris N. (2011). Fifty years of obsidian hydration dating in archaeology. *Journal of Non-Crystalline Solids* 357 (10), 2011-2023.

McDougall J. M., Tarling D. H., Warren S. E. (1983). The magnetic sourcing of obsidian samples from Mediterranean and near Eastern sources. *Journal of Archaeological Science* 10, 441-452.

1  
2 Mameli V., Musinu A., Niznansky D., Peddis D., Ennas G., Ardu A., Lugliè C., Cannas C. (2016).

3  
4 Much More than a Glass: The Complex Magnetic and Microstructural Properties of Obsidian, Journal  
5 of Physical Chemistry C, 120 (48), 27635-27645. doi:10.1021/acs.jpcc.6b08387  
6  
7

8  
9  
10  
11  
12  
13 Poupeau G., Le Bourdonnec F. X., Dubernet S., Scorzelli R. B., Duttine M., Carter T. (2007).

14  
15 Tendances actuelles dans la caractérisation des obsidiennes pour les études de provenance,  
16 ArchéoSciences, 31, 79-86.  
17  
18

19  
20  
21  
22  
23  
24 Quero T. (2014). The early Bronze Age site of Eia (Parma). Traces in Time n. 4, 1-5.  
25

26  
27  
28  
29  
30 Renfrew C., Cann J. R., Dixon J. E. (1965). Obsidian in the Aegean, Ann. British School Athens 60,  
31 225.  
32  
33

34  
35  
36  
37  
38  
39 Rochette P., Gattacceca J., Devouard B., Moustard F., Bezaeva N.S., Cournède C., Scaillet B. (2015).

40  
41 Magnetic properties of tektites and other related impact glasses. Earth and Planetary Science Letters  
42 432, 381-390.  
43  
44  
45

46  
47  
48  
49  
50 Scorzelli R.B., Petrick S., Rossi A.M., Poupeau G., Bigazzi G. (2001). Obsidian archaeological  
51 artefacts provenance studies in the Western Mediterranean basin: an approach by Mossbauer  
52 spectroscopy and electron paramagnetic resonance, Comptes rendus de l'académie des sciences, série  
53 ii, fascicule a - sciences de la terre et des planètes 332 (12), 769-77.  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

Stewart S.J., Cernicchiaro G., Scorzelli R.B., Poupeau G., Acquafredda P., De Francesco A. (2003).

Magnetic properties and <sup>57</sup>Fe Mössbauer spectroscopy of Mediterranean prehistoric obsidians for provenance studies. *Journal of Non-Crystalline Solids*, 323, 188-192.

Thorpe O.W., Warren S.E., Barfield L.H. (1979). The sources and distribution of archaeological obsidian in Northern Italy. *Preistoria Alpina*, 15, 73-92.

Tarling D. H., Hrouda F. (1993). *The Magnetic Anisotropy of Rocks*. London, Glasgow, New York, Tokyo, Melbourne, Madras: Chapman & Hall.

Tykot R.H. (1996). Obsidian procurement and distribution in the Central and Western Mediterranean. *Journal of Mediterranean Archaeology*, 9, 39-82.

Tykot R. H. (2002). Chemical Fingerprinting and Source Tracing of Obsidian: The Central Mediterranean Trade in Black Gold. *Accounts on Chemical Research* 35, 618–627. doi: 10.1021/ar000208

Urrutia Fucugauchi, J. (1999). Preliminary results of a rock-magnetic study of obsidians from central Mexico. *Geofisica International*, 38, 83-94.

Vásquez C.A., Nami H., Rapalini A. (2001). Magnetic sourcing of obsidians in Southern South America: some successes and doubts. *Journal of Archaeological Science*, 28, 613-618.

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

Venturino Gambari M. (1988). Alessandria, loc. Cascina Chiappona. Saggio di accertamento in area di insediamento di età preistorica (tavv. XIII-XIV). Quaderni della Soprintendenza del Piemonte 7, 43-53.

Venturino Gambari M. (1993). Casalnoceto, loc. Cascina Cascinetta. Strutture di abitato del Neolitico medio (tavv. LXXXVIII – XC). Quaderni della Soprintendenza del Piemonte, 11, 195-225.

Venturino Gambari M. (2004). Alla conquista dell'Appennino: le prime comunità delle valli Curone, Grue e Ossona. Omega Edizioni, Torino.

Weaver I., Sternberg R., Tykot R. H. (2009). Magnetic fingerprinting of Central Mediterranean obsidian source groups. In AGU Spring Meeting Abstracts 1, 4.

Zanella E., Ferrara E., Bagnasco L., Ollà A., Lanza R., Beatrice C. (2012). Magnetite grain-size analysis and sourcing of Mediterranean obsidians, *Journal of Archaeological Science* 39 (5), 1493–1498.

## Figure captions

1  
2  
3  
4  
5 Fig. 1. Map of Italy with the location of the obsidian samples collected from six Neolithic  
6 archaeological sites situated in Northern Italy. The main Mediterranean obsidian sources are also  
7  
8 indicated.  
9  
10

11  
12  
13  
14  
15  
16 Fig. 2. Obsidian archaeological tools found at the archaeological site of Parma (via Guidorossi).  
17  
18

19  
20  
21  
22  
23 Fig. 3. Isothermal acquisition curves obtained at ambient (293 K) and liquid nitrogen (77 K)  
24 temperatures for representative a-c) geological and d-f) archaeological samples.  
25  
26

27  
28  
29  
30  
31 Fig. 4. Examples of hysteresis cycles at 293 K and 77 K for geological samples from a) Lipari, b)  
32 Palmarola, c) Sardinia SC, and archaeological samples d-l) from several archaeological sites in  
33  
34 Northern Italy.  
35  
36

37  
38  
39  
40  
41  
42 Fig. 5. King plot, showing the anhysteretic susceptibility,  $\chi_a$ , vs. low-field magnetic susceptibility,  $\chi$ ,  
43 from the archaeological samples studied here and the geological obsidians from several  
44  
45 Mediterranean sources (Zanella et al., 2012).  
46  
47  
48

49  
50  
51  
52  
53 Fig. 6. Three-dimensional graphs comparing the magnetic parameters of geological samples from  
54 volcanic islands of the Mediterranean and archaeological samples from a) Parma; b) Brignano  
55  
56 Frascata, Cascina Chiappona, Casalnoceto and Garbagna (samples Ossi, Table 1) and c) Castello  
57  
58 d'Annone.  
59  
60  
61  
62  
63  
64  
65

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

Fig. 7. Dendrograms obtained after cluster analysis (Euclidean distance) of the magnetic parameters for a) the geological samples from various Mediterranean sources; b) geological obsidians and archaeological samples from Parma; c) geological obsidians and archaeological samples from Piedmont sites of Garbagna, Cascina Chiappona, Brignano Frascata, and Casalnoceto archaeological sites; d) geological obsidians and archaeological samples from Piedmont site of Castello d'Annone.

## Table captions

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

Table 1. Magnetic data of the archaeological obsidian samples.

Columns: Name of the archaeological site; Sample code; Mass in g;  $\chi$  = low-field magnetic susceptibility;  $\chi_a$  = anhysteretic magnetic susceptibility;  $Q_a = \chi_a / \chi$  susceptibility ratio,  $SIRM_{293}$  = saturation of isothermal remanence magnetization at 293K;  $SIRM_{77}$  = saturation of isothermal remanence magnetization at 77K,  $S_{T77/293} = SIRM$  ratio;  $M_R / M_S$  = magnetic remanence to saturation ratio;  $P$  = anisotropy degree of the magnetic susceptibility.

Table 2. Magnetic data of geological samples from several Mediterranean obsidian sources. Revised results from Zanella et al. (2012). Columns as in Table 1.

Table I

Archaeological Site	Sample	Mass (g)	$\chi$ ( $10^{-8} \text{ m}^3 \text{ kg}^{-1}$ )	$\chi_a$ ( $10^{-7} \text{ m}^3 \text{ kg}^{-1}$ )	$Q_a = \chi_a / \chi$	SIRM <sub>293</sub> ( $10^{-4} \text{ Am}^2 \text{ kg}^{-1}$ )	SIRM <sub>77</sub> ( $10^{-4} \text{ Am}^2 \text{ kg}^{-1}$ )	S <sub>T</sub>	M <sub>R</sub> /M <sub>S</sub>	P
Garbagna	Ossi 6	0.266	19.75	2.70	1.37	35.64	128.95	3.60	0.17	1.19
Cascina Chiappona	Ossi 7	0.385	14.56	2.06	1.41	34.54	105.46	3.10	0.19	1.28
	Ossi 8	0.079	8.39	1.43	1.71	17.60	49.37	2.80	0.19	1.03
	Ossi 9	0.109	17.47	2.71	1.55	40.18	137.61	3.40	0.17	1.04
Brignano Frascati	Ossi 10	0.604	81.80	63.38	7.75	319.54	913.91	2.90	0.25	1.21
	Ossi 11	0.287	38.73	8.46	2.18	109.41	223.69	2.00	0.24	1.25
	Ossi 12	0.813	6.03	0.12	0.19	0.039	0.086	2.20	0.02	1.10
Casalnoceto	Ossi 13	0.277	9.26	1.45	1.57	16.86	66.24	3.90	0.18	1.06
	Ossi 14	0.235	88.11	24.11	2.74	371.49	631.91	1.70	0.28	1.06
	Ossi 15	0.159	11.66	1.98	1.67	23.71	99.06	4.20	0.18	1.07
	Ossi 16	0.114	12.00	2.15	1.79	25.26	109.65	4.30	0.17	1.04
	Ossi 17	0.217	15.50	2.41	1.55	30.28	101.38	3.30	0.17	1.14
	Ossi 18	0.219	15.11	2.84	1.88	28.90	125.11	4.30	0.18	1.06
	Ossi 19	1.953	15.43	2.88	1.87	38.50	140.30	3.60	0.25	1.03
	Ossi 20	4.150	82.16	17.99	2.19	650.53	939.66	1.44	0.36	1.06
Castello D'Annone	CDA I	0.547	14.81	==	==	==	==	==	0.19	1.12
	CDA II	0.222	63.96	18.7	2.92	139.64	340.99	2.44	0.25	1.03
	CDA III	0.299	39.80	9.3	2.33	64.88	203.68	3.14	0.29	1.03
	CDA IV	0.288	111.46	16.2	1.45	227.43	920.14	4.05	0.17	1.05
	CDA V	0.174	34.48	15.5	4.51	51.72	228.16	4.41	0.13	1.01
	CDA 1	0.384	30.74	9.30	3.02	44.54	80.75	1.81	0.12	1.01
	CDA 2	0.091	130.17	9.25	0.71	339.09	1192.30	3.52	0.16	1.02
	CDA 3	0.081	110.93	16.16	1.46	327.87	1664.00	5.08	0.15	1.03
	CDA 4	0.205	140.31	15.54	1.11	265.03	1373.87	5.18	0.13	1.02
	CDA 5	0.078	123.65	9.29	0.75	217.67	725.14	3.33	0.12	1.05
	CDA 6	0.161	118.35	44.23	3.74	267.21	984.77	3.69	0.20	1.03
	CDA 7	1.029	100.44	18.99	1.89	266.17	972.97	3.66	0.21	1.06
	CDA 8	0.136	41.20	20.43	4.96	82.77	232.50	2.81	0.22	1.06
	CDA 9	0.132	70.37	13.41	1.91	175.56	535.75	3.05	0.15	1.06
	CDA 10	0.096	159.46	23.44	1.47	334.55	1286.40	3.85	0.14	1.07
	CDA 11	0.260	60.40	18.21	3.01	151.95	500.10	3.29	0.24	1.09
	CDA 12	0.334	30.55	13.87	4.54	38.31	74.58	1.95	0.19	1.09
CDA 13	0.128	145.77	19.34	1.33	289.18	1056.43	3.65	0.12	1.09	
CDA 14	0.021	111.00	32.16	2.90	590.25	1414.09	2.40	0.14	1.10	
CDA 15	0.140	72.86	16.35	2.24	165.71	637.14	3.84	0.16	1.08	
CDA 16	0.019	213.54	10.74	0.50	584.90	2432.29	4.16	0.11	1.09	
CDA 17	0.035	795.98	14.98	0.19	4482.76	5804.60	1.29	0.42	1.05	
Parma via Guidorossa	GUI 37	0.311	13.897	1.43	1.03	57.60	139.99	2.43	0.10	1.07
	GUI 38	0.367	11.559	1.25	1.08	24.09	103.81	4.31	0.15	1.04
	GUI 39	0.303	11.716	1.52	1.30	27.22	106.57	3.92	0.14	1.03
	GUI 40	0.110	8.545	0.55	0.64	23.50	57.06	2.43	0.15	1.03
	GUI 41	0.424	17.684	1.97	1.11	45.10	153.48	3.40	0.23	1.09
	GUI 43	0.123	15.528	2.01	1.29	33.64	115.91	3.45	0.13	1.03
	GUI 44	0.426	10.561	1.78	1.68	42.92	98.50	2.30	0.22	1.05
	GUI 45	0.354	7.068	1.09	1.55	25.59	53.95	2.11	0.23	1.03
	GUI 46	0.223	19.045	2.10	1.10	64.19	165.19	2.57	0.12	1.07



	GUI 47	0.142	10.282	1.24	1.21	29.89	101.47	3.40	0.16	1.06
	GUI 49	0.161	15.627	1.31	0.84	32.41	120.45	3.72	0.19	1.09
	GUI 50	0.219	12.466	0.86	0.69	116.94	379.98	3.25	0.11	1.06
	GUI 51	0.626	12.414	1.01	0.82	25.55	90.53	3.54	0.11	1.13
	GUI 54	0.056	43.786	6.01	1.37	150.16	358.81	2.39	0.19	1.04
	GUI 59	0.296	12.946	1.37	1.06	25.98	55.81	2.15	0.17	1.09
	GUI 61	0.049	39.755	2.44	0.61	209.31	312.94	1.50	0.24	1.02
	GUI 63	0.096	16.458	1.21	0.74	41.09	142.15	3.46	0.11	1.05
	GUI 64	1.100	23.609	2.48	1.05	66.08	193.79	2.93	0.15	1.20
	GUI 67	0.443	14.253	1.25	0.88	37.75	127.89	3.39	0.13	1.12
	GUI 68	0.148	6.486	0.64	0.98	18.24	50.13	2.75	0.13	1.04

Table II

	Sample	Mass (g)	$\chi$ ( $10^{-8} \text{m}^3 \text{kg}^{-1}$ )	$\chi_a$ ( $10^{-7} \text{m}^3 \text{kg}^{-1}$ )	$Q_a = \chi_a / \chi$	SIRM <sub>293</sub> ( $10^{-4} \text{Am}^2 \text{kg}^{-1}$ )	SIRM <sub>77</sub> ( $10^{-4} \text{Am}^2 \text{kg}^{-1}$ )	S <sub>T</sub>	M <sub>R</sub> /M <sub>S</sub>	P
Lipari Canneto	C2A1	4.38	7.70	0.85	1.10	10.90	41.98	3.85	0.08	1.04
	C2A2	2.42	20.40	2.16	1.06	45.12	108.75	2.41	0.08	1.05
	C4A1	3.33	17.60	2.26	1.28	33.19	95.83	2.89	0.06	1.03
	C4A2	2.95	20.20	2.28	1.13	18.33	71.44	3.90	0.07	1.08
Lipari Piano Conte	PC2B1	3.86	25.20	2.33	0.92	58.54	210.41	3.59	0.10	1.06
	PC2B2	3.56	47.50	5.60	1.18	117.25	321.25	2.74	0.10	1.08
	PC2B3	3.84	12.80	1.16	0.91	25.38	110.00	4.33	0.05	1.08
	PC3B1	3.27	28.00	2.87	1.03	61.19	252.86	4.13	0.07	1.06
	PC3B2	2.82	7.40	0.96	1.30	14.24	49.03	3.44	0.06	1.06
Lipari Diana	D2B1	3.28	16.40	2.29	1.40	22.48	71.98	3.20	0.06	1.05
	D2B2	2.75	15.30	4.30	2.81	53.69	116.54	2.17	0.06	1.05
	D1B1	4.35	18.90	3.99	2.11	68.71	161.43	2.35	0.15	1.01
	D1B2	3.23	30.90	3.44	1.11	59.16	143.71	2.43	0.12	1.06
	D1B3	3.04	9.00	1.23	1.37	18.32	63.30	3.46	0.09	1.07
Palmarola	Pa3B1	3.96	79.20	21.85	2.76	257.32	617.04	2.40	0.13	1.03
	Pa3B2	3.74	58.70	13.99	2.38	248.73	600.18	2.41	0.12	1.06
	Pa3B3	1.78	74.30	19.04	2.56	287.41	524.48	1.82	0.13	1.04
	Pa3B4	3.62	62.50	11.28	1.80	304.86	524.05	1.72	0.15	1.11
	Pa5B	3.40	60.70	13.96	2.30	254.64	487.62	1.91	0.18	1.04
Pantelleria	Pan1	1.95	14.50	0.60	0.41	0.93	1.28	1.37	0.01	1.01
	Pan2	2.91	14.90	0.37	0.25	0.76	1.10	1.44	0.01	1.01
	Pan3	2.73	15.90	0.54	0.34	1.54	3.16	2.04	0.01	1.01
Melos	B1A1	2.80	76.00	19.96	2.63	205.15	212.48	1.04	0.13	1.19
	B1A2	5.19	59.00	13.83	2.34	175.85	215.47	1.23	0.14	1.13
	B1A3	4.82	63.40	13.79	2.18	162.66	189.54	1.17	0.12	1.20
	B4B1	3.57	56.10	12.70	2.26	131.00	175.27	1.34	0.12	1.14
	B4B2	5.53	69.00	17.96	2.60	131.59	168.53	1.28	0.12	1.20
Mt. Arci SA	SAA1	2.34	18.50	6.21	3.36	56.31	102.77	1.83	0.08	1.15
	SAA2	2.75	24.50	5.95	2.43	74.32	173.65	2.34	0.11	1.13
	SAA3	1.36	26.80	8.26	3.08	85.74	176.38	2.06	0.09	1.17
	SAA4	3.59	15.20	4.32	2.84	41.02	92.65	2.26	0.01	1.15
Mt. Arci SB1	SB1B1	2.98	313.10	190.80	6.09	943.82	864.61	0.92	0.29	1.16
	SB1B2	2.62	403.10	254.90	6.32	1433.92	1094.51	0.76	0.29	1.17
	SB1B3	4.22	126.40	67.20	5.32	916.49	937.30	1.02	0.29	1.13
Mt. Arci SB2	SB2A1	2.98	92.60	25.50	2.75	185.73	410.60	2.21	0.09	1.11
	SB2A2	2.25	72.00	19.20	2.67	256.88	611.46	2.38	0.08	1.14

	SB2A3	3.71	72.70	17.00	2.34	155.95	377.03	2.42	0.08	1.22
Mt. Arci SC	SCB1	3.67	119.70	457.60	38.23	440.30	574.00	1.30	0.20	1.07
	SCB2	1.85	116.20	433.80	37.33	838.26	1132.83	1.35	0.20	1.03
	SCB3	3.77	122.20	269.90	22.09	595.48	666.19	1.12	0.20	1.08