

ISTITUTO NAZIONALE DI RICERCA METROLOGICA Repository Istituzionale

Thermodynamic transport theory of spin waves in ferromagnetic insulators

| • |
|---|
|---|

Original

Thermodynamic transport theory of spin waves in ferromagnetic insulators / Basso, Vittorio; Ferraro, Elena; Piazzi, Marco. - In: PHYSICAL REVIEW. B. - ISSN 2469-9950. - 94:14(2016). [10.1103/PhysRevB.94.144422]

Availability: This version is available at: 11696/54605 since: 2021-03-01T12:46:25Z

Publisher: APS

Published DOI:10.1103/PhysRevB.94.144422

Terms of use:

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

Publisher copyright American Physical Society (APS) Copyright © American Physical Society (APS)

(Article begins on next page)

Thermodynamic transport theory of spin waves in ferromagnetic insulators

Vittorio Basso,¹ Elena Ferraro,^{1,*} and Marco Piazzi¹

¹Istituto Nazionale di Ricerca Metrologica, Strada delle Cacce 91, 10135 Torino, Italy

(Dated: November 18, 2018)

We use the Boltzmann transport theory in the relaxation time approximation to describe the thermal transport of spin waves in a ferromagnet. By treating spin waves as magnon excitations we are able to compute analytically and numerically the coefficients of the constitutive thermomagnetic transport equations. As a main result, we find that the absolute thermo-magnetic power coefficient ϵ_M , relating the gradient of the potential of the magnetization current and the gradient of the temperature, in the limit of low temperature and low field, is a constant $\epsilon_M = -0.6419 k_B/\mu_B$. The theory correctly describes the low-temperature and magnetic-field dependencies of spin Seebeck experiments. Furthermore, the theory predicts that in the limit of very low temperatures the spin Peltier coefficient Π_M , relating the heat and the magnetization currents, tends to a finite value which depends on the amplitude of the magnetic field. This indicates the possibility to exploit the spin Peltier effect as an efficient cooling mechanism in cryogenics.

PACS numbers: 75.76.+j, 75.30.Ds, 85.75.-d, 05.70.Ln

I. INTRODUCTION

The thermal transport of spin waves is the key physical phenomenon at the basis of the longitudinal spin Seebeck effect $(LSSE)^1$, which is one of the most promising effect of spin caloritronics $^{2-4}$. In the LSSE a spin current is generated by a temperature gradient in a ferrimagnetic insulator like yttrium iron garnet (YIG) and it is detected by the inverse spin Hall effect in an adjacent Pt layer $^{5-9}$. This effect has been interpreted as the consequence of the presence of a spin current carried by non equilibrium spin waves (or magnons) in the ferrimagnetic insulator which is converted into a spin current carried by electrons in the metal 3,10,11 . The source of this conversion is the interaction between the d electrons in the ferromagnet and the s electrons in the metal which gives rise to an absorption of a magnon in the insulator and the corresponding generation of an electron spin flip in the metal $^{12-18}$. While the assessment of the interface is well documented in the literature $^{10,19-21}$, the description of the transport of non equilibrium spin waves inside the bulk ferromagnet is still a debated issue²²⁻²⁹.

The thermodynamic problem of the joint transport of heat and magnetic moment (thermo-magnetics) has its counterpart in the field of thermoelectricity where one has the joint transport of heat and charge. In the non equilibrium thermodynamics of fluxes and forces these joint transport problems are described by the identification of the current densities of the extensive variables of interest with their associated thermodynamic forces. While in the field of thermoelectricity it is well assessed that the gradient of the electric potential ∇V_e is the force associated to the electric current density j_e and the temperature gradient ∇T is the force associated to the heat current j_q , in the field of thermo-magnetics there is controversy regarding the thermodynamic forces to employ. The reason is related to the correct determination of the relations between the thermodynamic description and the microscopic details of the processes.

For what concerns the temperature variable, while for static magnetic properties the thermodynamic temperature is assumed to be the correct one^{30} , for the transport properties the question has not an obvious answer. The problem dates back to the 1977 paper of Sanders and Walton³¹ discussing the reasons for the elusive contribution of magnons to the total heat conductivity of magnetic materials. Sanders and Walton noted that the magnon subsystem could be partially isolated from the phonon one and described the equilibration of the temperatures of the two subsystems by means of the finite relaxation time τ_{mp} . In the limit of very long relaxation times, the two temperatures are different and only the phonon heat transport could be experimentally observed, while, if τ_{mp} is short enough, the two temperatures coincide with the thermodynamic temperature and the magnon heat transport can be observed. When, more recently, this picture was applied to the spin Seebeck effect, it turned out that, assuming partial decoupling, most of the transport effects could just be described as proportional to the difference between the temperature of the magnons in the ferromagnet and the temperature of the electrons in the metal^{10,19-21}. This approach has been successful to describe the proportionality of the injected spin current on the temperature gradient, but it was unable to correctly reproduce the experimental dependence on the thickness of YIG³², therefore showing the necessity to take into account also the bulk and not only the interface. Stimulated also by the experimental results of Ref.[33], showing that in YIG there exists a close spatial correspondence between magnons and phonons temperatures, other authors have used the gradient of the thermodynamic temperature as a driving force $^{22-26,28}$, therefore assuming a good thermal coupling between the two subsystems. It is worth to mention that Sanders and Walton³¹ in their original paper already demonstrated that, for YIG, magnons and phonons could exchange energy with a quite short time constant τ_{mp} . However, as τ_{mp} may be material dependent and not too

small, the general case, which gives rise to non trivial coupled phonon-magnon heat flow, is indeed of interest and it has been treated in Ref.[34]. In the limit of very small τ_{mp} the picture simplifies and the phonon and magnon heat flows can be just linearly summed up.

Much more subtle is the choice of the thermodynamic force to be associated with the magnetic moment current. Refs. [22-25, and 28] have used the gradient of the magnon accumulation as a force. This approach, while microscopically correct, suffers for the problem that, in non equilibrium thermodynamics, the current of an extensive variable should be always associated to the gradient of an intensive variable. This effective force has been worked out in the thermodynamic theory of Johnson and Silsbee³⁵. In their approach the potential for the magnetization current is derived from purely thermodynamic grounds and it results to be given by $H^* = H - H_{ea}$, the difference between the magnetic field H and the field $H_{eq}(M)$ corresponding to the equation of state at equilibrium²⁹. When the theory of Johnson and Silsbee is applied to the problem of the transport of magnons, one finds that the potential H^* is directly related to the chemical potential μ_m associated with the magnon accumulation, that is $H^* = \mu_m/(2\mu_0\mu_B)$. It is worth to notice that the gradient of the chemical potential of magnons is also used in the very recent publication of Ref. [36].

In the present paper we apply the Boltzmann transport equation to magnons by using the gradient of the Johnson and Silsbee potential ∇H^* as the driving force for the magnetization current and the gradient of the thermodynamic temperature ∇T as the driving force for the heat current. By performing the calculations in the relaxation time approximation, we are able to derive all the kinetic coefficients of the constitutive equations. In particular we are able to obtain the expressions for the temperature and magnetic field dependences of the kinetic coefficients. These expressions have closed analytical forms in the low temperature limit, where the quadratic dispersion relation for magnons holds, and they can be computed numerically, by assuming isotropic behavior, in the high temperature range.

As a main result we find that the absolute thermomagnetic power coefficient ϵ_M , relating ∇H^* and ∇T , is independent of the magnon scattering mechanism and its value, in the limit of low field, is the constant $\epsilon_M =$ $-0.6419 k_B/\mu_B$. Moreover, we predict that the spin Peltier coefficient Π_M , relating the heat and the magnetization currents, tends, at very low temperatures, to the finite value $\Pi_M = -\mu_0 H_0$, which depends on the amplitude of the magnetic field H_0 . This feature indicates the possibility to exploit the spin Peltier effect as an efficient cooling mechanism in the cryogenic temperature range. Finally we make a preliminary test of the model by inserting the parameters of YIG and computing the values of the spin Seebeck effect. By comparing with experiments at low temperature, we find that the theory correctly describes both the temperature and the magnetic field dependences of the spin Seebeck coefficient for

the bulk $case^{37}$.

The paper is organized as follows. Section II presents the main features of the Johnson and Silsbee theory. Section III introduces the spin waves in equilibrium under a non zero chemical potential. The Boltzmann transport equation is described in Section IV and the main results are presented in Section V. The application of the theory to the spin Seebeck effect is described in Section VI. Finally, the features and the limitations of the theory are shortly discussed in Section VII. All the technical and mathematical aspects are detailed in the Appendices A and B.

II. THERMO-MAGNETIC TRANSPORT EQUATIONS

We consider a magnetic system in which the macroscopic magnetization vector M and the magnetic field H are parallel and directed along an easy axis that can be due, for example, to an anisotropic crystal structure. Therefore we describe the system by the scalar amplitudes M and H. By following the Johnson and Silsbee approach^{29,35}, the thermodynamics of the ferromagnet is formulated by expressing the variation of the non equilibrium system enthalpy $u_e(s, H; M)$ as a function of the entropy density s, of the magnetic field H and of the magnetization M:

$$du_e = Tds - \mu_0 M dH - \mu_0 H^* dM. \tag{1}$$

In the previous expression T is the thermodynamic temperature, μ_0 is the permeability of vacuum and $H^* = H - H_{eq}$ is the affinity associated to the change of the magnetization, with $H_{eq}(M)$ being the equation of state for the magnetic field at equilibrium. H^* is different from zero when the system is locally out-of-equilibrium. Relaxation toward equilibrium is described by assuming linear system behavior. The relaxation equation is given by the proportionality between the rate of change of the magnetization dM/dt, a generalized velocity, and H^* , a generalized force. By generalizing this treatment to spatially extended systems in which magnetization currents j_M may be present, the relaxation equation becomes the continuity equation for the magnetization

$$\frac{\partial M}{\partial t} + \nabla \cdot \boldsymbol{j}_M = \frac{H^*}{\tau_M}.$$
(2)

The right hand side of Eq.(2) expresses the presence of sources and sinks in the system, giving rise to the non conservation of the magnetization, and it contains a phenomenological time constant τ_M . Beyond its continuity equation, every medium is also characterized by its constitutive equations describing how the magnetization and the heat currents depend on the gradients of the associated intensive variables. Within this approach the relevant gradients are ∇T , which is associated to the heat current j_q , and ∇H^* , which is associated to the magnetization current j_M . By considering linear behavior and limiting to one dimension, the equations are

$$j_M = \sigma_M \,\mu_0 \nabla H^* - \epsilon_M \sigma_M \,\nabla T \tag{3}$$

$$j_q = \epsilon_M \sigma_M T \mu_0 \nabla H^* - (\kappa + \epsilon_M^2 \sigma_M T) \nabla T.$$
 (4)

In Eqs.(3) and (4) $\nabla \equiv \partial/\partial x$ and, in analogy with the thermoelectric effects^{38,39}, σ_M is the conductivity for the magnetization current, ϵ_M is the absolute thermomagnetic power coefficient and κ is the total thermal conductivity under zero magnetization current. When the constitutive equation (3) is solved together with the continuity equation (2), under given boundary conditions, the currents and the potential H^* can be computed and the typical diffusion length, $l_M = (\mu_0 \sigma_M \tau_M)^{1/2}$, results to be related to material dependent parameters 29 . In the spin Seebeck effect, in which the ferromagnetic material is subjected to a uniform temperature gradient ∇T , the magnetization current source is $j_{MS} = -\sigma_M \epsilon_M \nabla T$. The part of the current transmitted to the sensing layer depends on the coupling between the two materials and in particular it depends on the ratio $v_M = l_M / \tau_M$ between the diffusion length and the time constant of each layer²⁹.

All the parameters contained in the continuity equation (2) and the constitutive equations (3) and (4) can be calculated on the basis of a microscopic theory. In Sections III and IV we will compute them in the case of the magnons in a ferromagnet. For what concerns the thermal conductivity we will limit to compute the contribution from spin waves. In fact, as we assume that the magnetic subsystem is well thermally coupled with all the other degrees-of-freedom, the thermodynamic temperature is the only thermal intensive variable associated to the heat current. If there are many different types of carriers, i.e. magnons and phonons, the total thermal conductivity is just the sum of the individual contributions. Instead, when the magnetic subsystem is partially decoupled from the lattice, alternative methods, as those used in Ref.[34], can be applied.

III. STATISTICS OF MAGNONS

A. Spin waves

In a saturated ferromagnet, the local magnetic moments are all essentially parallel and the spin waves are the lowest energy excitations.

In a classical picture, the spin waves are plane waves formed by the small deviations of the magnetization vector M_{\perp} from its main direction M_{\parallel} . Due to the precession of magnetization around the magnetic field, M_{\perp} is a vector rotating in time in the plane perpendicular to M_{\parallel} with an angular velocity ω_q depending on the wavenumber q of the plane wave. Considering the relevant energy terms for a ferromagnet, the dispersion relation reads
$$\begin{split} \omega_{\boldsymbol{q}} &= -\gamma \mu_0 [(l_{ex}^2 q^2 + H_0) (l_{ex}^2 q^2 + H_0 + M_s \sin^2 \theta_q)]^{1/2} \text{ where } \\ \gamma &= -e/m_e \text{ is the gyromagnetic ratio for electrons, } l_{ex} \text{ is } \\ \text{the exchange length, } H_0 &= H_a + H_{AN} \text{ contains here contributions from the applied field } H_a \text{ and the anisotropy } \\ \text{field } H_{AN} \text{ along the easy axis, } M_s \text{ is the saturation magnetization, } q &= |\boldsymbol{q}| \text{ and } \theta_q \text{ is the angle formed by the } \boldsymbol{q} \\ \text{vector with the magnetization axis}^{40,41}. \text{ The exchange } \\ \text{length is related to the exchange stiffness } A \text{ by the relation } \\ l_{ex}^2 &= 2A/(\mu_0 M_s^2). \end{split}$$

In a quantum picture, the magnon is the quantum of the spin wave, it has energy $\epsilon(\mathbf{q}) = \hbar \omega_{\mathbf{q}}$ and, in the case of magnetism due to the electron spin, it carries a magnetic moment of $-2\mu_B$, where $\mu_B = e\hbar/(2m_e)$ is the Bohr magneton. Having an integer spin, magnons obey the Bose-Einstein statistics described by the distribution

$$g_0(\boldsymbol{q}) = \frac{1}{\exp\left(\epsilon(\boldsymbol{q})/(k_B T)\right) - 1},\tag{5}$$

where k_B is the Boltzmann constant. All the relevant informations on the system are contained in the magnon energy dispersion relation $\epsilon(\mathbf{q})$. At low q it is possible to approximate the dispersion relation as

$$\epsilon(\boldsymbol{q}) \simeq Dq^2 + \epsilon_H,\tag{6}$$

where $D = 4Aa^3$ is the stiffness constant of the spin waves, with a being the interatomic distance³⁹, and $\epsilon_H = 2\mu_0\mu_BH_0^{41}$. Eq.(6) is valid when the magnetostatic energy term can be disregarded with respect to the other terms. The magnon energy is expected to show deviations from Eq.(6) at large q when the wavelength approaches the interatomic distance. Specific deviations depend on the type of crystal lattice³⁹. An isotropic extension of the dispersion relation for large q is considered in Appendix A.

B. Equilibrium thermal magnons

The equilibrium properties of a ferromagnet, like the magnetization and the specific heat capacity, can be directly obtained from the statistics of magnons^{39,40,42}. The method consists in evaluating the statistical average of the corresponding physical quantities (the magnetic moment, the energy) weighted over the distribution given by Eq.(5) and integrated over the space Σ of the admissible wavenumbers \boldsymbol{q} . For example, the average magnetization is given by the integral

$$M = M_0 - 2\mu_B \frac{1}{(2\pi)^3} \int_{\Sigma} g_0(\mathbf{q}) d^3 q, \qquad (7)$$

where M_0 is the spontaneous magnetization at zero temperature given by $M_0 = n\mu_B$, with *n* being the density of elementary magnetic moments. The integration is performed by standard methods (see Appendix A) and the result can be written as

$$M = M_0 \left(1 - \frac{1}{2\pi^2} t^{3/2} A_0 \right), \tag{8}$$

where $t = T/T_m$ is the dimensionless temperature, with $T_m = D/(a^2k_B)$ giving the temperature scale of the problem. By following an equivalent method for the specific heat $c_m = \partial u_m / \partial T$ the result is

$$c_m = nk_B \frac{5}{8} \frac{1}{\pi^2} t^{3/2} A_1.$$
(9)

Eqs.(8) and (9) contain the well know result that the low temperature behavior of M and c_m is a $T^{3/2}$ power law. Furthermore additional dependence on the temperature and field is contained in the dimensionless coefficients A_r (r = 0, 1, ...), which contain a dependence on the ratio h/t, where $h = 2\mu_0\mu_B H_0/(k_B T_m)$ is the dimensionless magnetic field. The definition of the coefficients A_r is reported in Appendix A, Eq.(A1).

C. Relaxation of thermal magnons

When the number of magnons is different from the equilibrium value of Section III A (see Eq.(5)), one describes their distribution as

$$g_0(\boldsymbol{q}, \mu_m) = \frac{1}{\exp\left((\epsilon(\boldsymbol{q}) - \mu_m)/(k_B T)\right) - 1},$$
 (10)

by introducing a non zero chemical potential μ_m . Considering that the magnetization can change only because the number of magnons n_m changes, $dM = -2\mu_B dn_m$, by using Eq.(1) with dH = 0, one finds that $\mu_m =$ $\partial u_e/\partial n_m = 2\mu_0\mu_B H^*$. This shows that for an insulating ferromagnet the chemical potential associated with the magnons, μ_m , is equivalent to the Johnson and Silsbee potential H^* . Every time the potential H^* is different from zero, the distribution of magnons is given by Eq.(10). The equilibrium distribution $g_0(\boldsymbol{q}, 0)$ of Eq.(5) is recovered when $H^* = 0^{43}$. To describe how the distribution $g_0(\mathbf{q}, \mu_m)$ of Eq.(10) relaxes to the distribution $g_0(\boldsymbol{q},0)$ of Eq.(5), one has to state a relaxation equation. As the time dependence can be only in the chemical potential, i.e. $\mu = \mu_m(t)$, a reasonable assumption is to consider the relaxation rate toward equilibrium to be proportional to the distance from equilibrium itself. Therefore the equation for $\mu_m(t)$ is $\partial \mu_m / \partial t = -\mu_m / \tau_r$, where τ_r is the magnon relaxation time constant describing the generation and annihilation of magnons. The relaxation equation for the distribution $g_0(\boldsymbol{q}, \mu_m)$ is then

$$\frac{\partial g_0(\boldsymbol{q},\mu_m)}{\partial t} = -\frac{g_0(\mu_m) - g_0(0)}{\tau_r}.$$
 (11)

For a spatially homogeneous system the continuity equation (2), with $\mathbf{j}_M = 0$, becomes simply $\partial M/\partial t = H^*/\tau_M$. As from Eq.(11) it is possible to derive the same equation, we are able to establish a relation between the macroscopic and the microscopic relaxation times, τ_M and τ_r respectively. On the right hand side of Eq.(11), if $g_0(\mu_m)$ is very close to $g_0(0)$ we can express their difference as $g_0(\mu_m) - g_0(0) \simeq -\mu_m \partial g_0(0) / \partial \epsilon$ and Eq.(11) becomes

$$\frac{\partial g_0(\boldsymbol{q}, \mu_m)}{\partial t} = \frac{\mu_m}{\tau_r} \frac{\partial g_0(\boldsymbol{q}, 0)}{\partial \epsilon}.$$
 (12)

By performing the statistical average of both sides of Eq.(12) and multiplying by $-2\mu_B$, we obtain $\partial M/\partial t$ at the left hand side. Then by using $\partial M/\partial t = H^*/\tau_M$ we obtain the expression for τ_M as

$$\frac{1}{\tau_M} = -\mu_0 (2\mu_B)^2 \frac{1}{(2\pi)^3} \int_{\Sigma} \frac{1}{\tau_r} \frac{\partial g_0(0)}{\partial \epsilon} d^3 q, \qquad (13)$$

which is the sought relation. By comparing Eq.(13) with the definition of the magnetization of Eq.(8), it turns out the additional relation $\tau_M = \tau_r / \chi$, where $\chi = \partial M / \partial H_0$. The expression for the time constant τ_M of Eq.(13) can be integrated (see Appendix A), giving as a result

$$\tau_M = \frac{\tau_r}{m} 2\pi^2 t^{-1/2} (-A_0')^{-1}, \qquad (14)$$

where $m = 2\mu_0\mu_B M_0/(k_B T_m)$ is a dimensionless parameter depending on the spontaneous magnetization M_0 and A'_0 is a dimensionless coefficient defined in Appendix A, Eq.(A2).

IV. TRANSPORT OF NON EQUILIBRIUM MAGNONS

A. Boltzmann transport equation

On the basis of what shown in Section III we can describe the accumulation of magnons by means of the chemical potential μ_m . The non equilibrium distribution $g(\mathbf{q}, \mu_m)$, which is realized in presence of the gradients $\nabla \mu_m$ and ∇T , can be derived by the Boltzmann transport equation

$$\frac{\partial g}{\partial t} + \nabla_{\boldsymbol{q}} g \cdot \frac{\partial \boldsymbol{q}}{\partial t} + \nabla_{\boldsymbol{r}} g \cdot \frac{\partial \boldsymbol{r}}{\partial t} = \left. \frac{\partial g}{\partial t} \right|_{collisions}.$$
 (15)

In the most general case, to describe both stationary and non stationary states, the collision term at the right hand side of Eq.(15) should take into account both magnon conserving and non-conserving events.

In the present Section we are interested to derive the behavior under stationary states, therefore we limit to describe the relaxation processes in which the value of the chemical potential μ_m of Eq.(10) is constant in time.

We can evaluate the right hand side of Eq.(15), in the relaxation time approximation, as

$$\left. \frac{\partial g}{\partial t} \right|_{collisions} = -\frac{g(\boldsymbol{q}, \mu_m) - g_0(\boldsymbol{q}, \mu_m)}{\tau_c}, \qquad (16)$$

where τ_c is the relaxation time associated to the collision events conserving the number of magnons and g_0 is the local distribution under constrained μ_m . Eq.(15) with the relaxation time approximation of Eq.(16) describes how fast the non equilibrium distribution $g(\mathbf{q}, \mu_m)$ decays into $g_0(\mathbf{q}, \mu_m)$.

It is worth to notice that from Eq.(15) it is also possible to derive Eq.(12), describing the relaxation from $g_0(\mathbf{q}, \mu_m)$ to $g_0(\mathbf{q}, 0)$, as a special case. Indeed, in that case one fixes the distribution shape $g = g_0$ of Eq.(10) and let the chemical potential μ_m to change in time. However, as the distribution shape is already the equilibrium one g_0 , then a collision term like Eq.(16) would have no effect. This is expected, because microscopic events contributing to the relaxation from $g_0(\mathbf{q}, \mu_m)$ to $g_0(\mathbf{q}, 0)$ are all events which do not conserve the number of magnons. Then the relaxation must be described by introducing a different term, as it has been done in Section III C, characterized by a different relaxation time τ_r . By following this route one obtains also Eq.(12) as a special limit of the general Eq.(15).

To solve the kinetic Boltzmann equation (15) for stationary states we put $\partial g/\partial t = 0$. The second term at the left hand side of Eq.(15) is evaluated by introducing the crystal momentum of magnons $\boldsymbol{p} = \hbar \boldsymbol{q}$ and by evaluating the associated force $\boldsymbol{F} = \partial \boldsymbol{p}/\partial t = (1/\hbar)\partial \boldsymbol{q}/\partial t$ as the gradient of the energy $\boldsymbol{F} = -\nabla_{\boldsymbol{r}}\epsilon$. The result is $\nabla_{\boldsymbol{q}}\boldsymbol{g} \cdot \partial \boldsymbol{q}/\partial t = -\boldsymbol{v} \cdot \nabla_{\boldsymbol{r}}\epsilon \ \partial g/\partial \epsilon$, where $\boldsymbol{v} = (1/\hbar)\nabla_{\boldsymbol{q}}\epsilon$ is the magnon group velocity. The third term at the left hand side is evaluated by using $\boldsymbol{v} = \partial \boldsymbol{r}/\partial t$. The resulting Boltzmann transport equation for magnons reads

$$g = g_0 - \tau_c \, \boldsymbol{v} \cdot \left(\nabla_{\boldsymbol{r}} g - \nabla_{\boldsymbol{r}} \epsilon \, \frac{\partial g}{\partial \epsilon} \right). \tag{17}$$

If the gradients are not so large, the second term at the right hand side is small and, in a first approximation, it can be evaluated at $g = g_0$ with g_0 given by Eq.(10). After a few passages we find the solution for the non equilibrium distribution of magnons in terms of the gradients of the intensive variables T and μ_m :

$$g \simeq g_0 + \tau_c \, \boldsymbol{v} \cdot \left[\nabla_{\boldsymbol{r}} \mu_m + (\epsilon - \mu_m) \frac{\nabla_{\boldsymbol{r}} T}{T} \right] \frac{\partial g_0}{\partial \epsilon}.$$
 (18)

For the previous solution we observe that the effect of the second term at the right hand side is to slightly change the shape of g_0 without changing the integral. Therefore the collision time τ_c can be interpreted as describing processes in which the number of magnons does not change.

B. Transport coefficients

The coefficients of the constitutive equations (3) and (4) can be calculated by expressing the magnetization and the heat currents in terms of the non equilibrium distribution of magnons g(q) given by the solution of the Boltzmann transport equation $(17)^{39,44}$. The two expressions, in vector form, are

$$\boldsymbol{j}_M = -2\mu_B \boldsymbol{j}_n = -2\mu_B \frac{1}{(2\pi)^3} \int_{\Sigma} \boldsymbol{v} \, g(\boldsymbol{q}) d^3 q \qquad (19)$$

$$\boldsymbol{j}_{q} = \boldsymbol{j}_{u} - \mu_{m} \boldsymbol{j}_{n} = \frac{1}{(2\pi)^{3}} \int_{\Sigma} \boldsymbol{v} \left(\epsilon - \mu_{m} \right) g(\boldsymbol{q}) d^{3} q. \quad (20)$$

By inserting the approximated solution Eq.(18) into the integrals Eqs.(19) and (20), we observe that only the second term of Eq.(18), containing the derivative of the Bose-Einstein distribution g_0 (Eq.(10)), is non zero. Moreover, by assuming to deal with an isotropic material and by taking both currents and forces along the x direction, the integrals of Eqs.(19) and (20) are simplified. Indeed, the tensor $v_i v_j$, where the index i corresponds to the component of the current and the index j to the component of the force, reduces to the scalar v_x^2 . The result of the integrations can be then directly written in terms of the coefficients of the constitutive equations (3) and (4). This way, we find the following expressions for the conductivity of the magnetization current

$$\mu_0 \sigma_M = \tau_{c_0} m v_m^2 \frac{1}{3\pi^2} t^{3/2} C_0, \qquad (21)$$

for the absolute thermo-magnetic power coefficient

$$\epsilon_M = -\frac{k_B}{2\mu_B} \frac{C_1}{C_0},\tag{22}$$

and for the thermal conductivity due to the magnon $\rm diffusion^{31,45}$

$$\kappa = nk_B\tau_{c_0}v_m^2 \frac{1}{3\pi^2} t^{5/2} \frac{C_0 C_2 - C_1^2}{C_0}.$$
 (23)

In the previous equations the parameter $v_m = (k_B T_m/m^*)^{1/2}$ gives the scale of the thermal velocity of the spin waves, $m^* = \hbar^2/(2D)$ is the magnon effective mass and C_r are coefficients defined in Appendix A, Eq.(A3). Since we are considering the possibility that the collision time τ_c may depend on the magnon wavenumber modulus q as $\tau_c = \tau_{c_0} f_c(q)$, where $f_c(q)$ is a normalized wavenumber dependence, equations (21) and (23) contain explicitly the constant τ_{c_0} , while $f_c(q)$ is included in the C_r definition.

V. RESULTS

The result of the magnon transport theory, developed in Sections III and IV, is represented by Eqs.(14) and (21-23), expressing the temperature and magnetic field dependences of the phenomenological time constant τ_M appearing in the continuity equation (2) and of the coefficients σ_M , ϵ_M and κ of the constitutive equations (3) and (4). Eqs.(14) and (21-23) depend on the coefficients A'_0 and C_r , defined by integrals over the space Σ of the admissible wavenumbers q that are calculated by standard methods (see Appendix A)⁴⁴.

At low temperature, i.e. $t \ll 1$, the coefficients can be computed by using the low q approximation given by Eq.(6) and the resulting analytical expressions for constant τ_c are reported in Appendices A and B and shown in Fig.1. The leading order dependence of the coefficients on the temperature t and on the field h is shown in Table I for $t \gg h$ and $t \ll h$. As a main result we find that the absolute thermo-magnetic power coefficient ϵ_M , in the limit $h \to 0$, is independent of τ_c and t and its value is $\epsilon_M = -(5/2)(\zeta(5/2)/\zeta(3/2))k_B/(2\mu_B)$, where $\zeta(\cdot)$ is the Riemann zeta function, so that $\epsilon_M = -0.6419 k_B/\mu_B$. By using $k_B/\mu_B = 1.49$ K T⁻¹ we obtain $\epsilon_M = -0.956$ K T^{-1} . This result shows that the magnon accumulation in terms of $\nabla \mu_m$ is directly related to the temperature gradient ∇T . Fig.1 also shows the behavior of the diffusion length l_M and of the ratio $v_M = l_M/\tau_M$ entering into the expression of the current which is transmitted into the sensing layer²⁹. The magnetization current source of the spin Seebeck effect $j_{MS} = -\epsilon_M \sigma_M \nabla T$ is shown in Fig.2. It depends on the conductivity σ_M which is determined by the scattering mechanism. The theory predicts a decrease of the current j_{MS} as a function of the field h, which is linear for low fields (see Fig.2 and Table I). This is an effect that was also observed in YIG/Pt spin Seebeck experiments, see Ref. [37], and it will be discussed in Section VI.

At high temperature, also the high wavenumbers of the spin waves are excited and the dispersion relation of Eq.(6) shall be modified in order to take into account that at high q the magnon energy reaches the maximum energy level $\epsilon = \epsilon_m + \epsilon_H$. Considering the isotropic expression given in Appendix A, the transport coefficients can be computed in the full temperature range up to $T = T_m$, i.e. t = 1. The integrals are performed by numerical methods. Fig.3 shows the temperature t and the field h dependences of the thermo-magnetic coefficients, while Fig.4 shows the current source j_{MS} as a function of the field h. The behavior of the coefficients at high t, obtained by taking a constant τ_c , does not present novel or intriguing features with respect to the low temperature case. The interesting physics of the high t behavior it is rather to be searched in the wavenumber dependence of the collision time for magnons $\tau_c(q)$. This aspect will be briefly discussed in Section VII.

Another temperature region that can be explored by the theory is the very low temperature region $t \ll h$. The results are shown in Table I. While most of the quantities goes to zero exponentially as soon as $t \to 0$, it is worth to observe the special behavior of ϵ_M and l_M which do not contain the exponential decay. The consequence of this fact can be appreciated by computing the spin Peltier coefficient Π_M , which is the proportionality coefficient between the heat and the magnetization currents, $j_q = \Pi_M j_M$. It can be derived from the constitutive equations (3) and (4) by imposing a constrained magnetization current and the condition $\nabla T = 0$. It results that $\Pi_M = \epsilon_M T$ and therefore, in the low q approximation, we have

$$\Pi_M = -\frac{k_B}{2\mu_B} \frac{C_1}{C_0} T.$$
 (24)

In the limit of very low temperature $t \ll h$ we know that $C_1/C_0 = 5/2 + h/t$ (see Table I) and thus

$$\Pi_M = -\left(\frac{5}{2}\frac{k_B T}{2\mu_B} + \mu_0 H_0\right).$$
 (25)

We see that as soon as the temperature approaches zero, $T \to 0$, the coefficient Π_M tends to the finite value $\Pi_M(0) = -\mu_0 H_0$. This indicates the possibility to employ the spin Peltier effect as an efficient cooling mechanism close to absolute zero. However, the low temperature efficiency of spin Peltier cooling is limited by the diffusion length l_M of the ferromagnet which is going to zero for $T \to 0$ as $l_M = l_{M_0} t^{1/2}$, with the normalization coefficient l_{M_0} defined in the caption of Fig.1. Since l_M is the typical length over which the magnetization current can develop, the cooled region will also shrink to zero in agreement with the third principle of thermodynamics³⁸. However, the slow decrease of l_M as the square root of the temperature gives the possibility to explore experimentally this effect in the cryogenic region.

VI. APPLICATION TO THE SPIN SEEBECK EFFECT

The knowledge of the kinetic coefficients allows to compute the spin current in a ferromagnet and to predict the amplitude of the spin Seebeck effect. Problems related to the passage of magnetization and heat currents between two adjacent media, including the spin Seebeck and the spin Peltier effects in YIG/Pt layers, can be well described within the Johnson and Silsbee approach^{29,35}.

To learn about the values of the parameters obtained in the theory, we need to insert typical values for the materials of interest. YIG is the most interesting material for the spin Seebeck effect and even if YIG is a ferrimagnet with a dispersion relation of several branches⁴³, we can apply the theory at low temperature where only the first branch is relevant. With a saturation magnetization of $M_0 = 1.96 \cdot 10^5$ A/m⁴¹ and a spin wave exchange stiffness of $D = 8.6 \cdot 10^{-40}$ Jm²⁴³, we have a

| | | limit $t \ll h$ | limit $t \gg h$ |
|-----------------------------|---|--|---|
| σ_M/σ_{M_0} | $\frac{1}{3\pi^2}t^{3/2}C_0$ | $\tfrac{1}{4\pi^{3/2}}t^{3/2}\exp\left(-\tfrac{h}{t}\right)$ | $\frac{\zeta(3/2)}{4\pi^{3/2}}t^{3/2}\left(1-\frac{2\pi^{1/2}}{\zeta(3/2)}\left(\frac{h}{t}\right)^{1/2}\right)$ |
| j_{MS}/j_{MS_0} | $\frac{1}{3\pi^2}t^{3/2}C_1$ | $\frac{1}{4\pi^{3/2}}t^{3/2}\left(\frac{5}{2}+\frac{h}{t}\right)\exp\left(-\frac{h}{t}\right)$ | $\frac{5\zeta(5/2)}{8\pi^{3/2}}t^{3/2}\left(1-\frac{3\zeta(3/2)}{5\zeta(5/2)}\left(\frac{h}{t}\right)\right)$ |
| $\epsilon_M/\epsilon_{M_0}$ | $\frac{C_1}{C_0}$ | $\frac{5}{2} + \frac{h}{t}$ | $\frac{5}{2} \frac{\zeta(5/2)}{\zeta(3/2)} \left(1 + \frac{2\pi^{1/2}}{\zeta(3/2)} \left(\frac{h}{t} \right)^{1/2} \right)$ |
| $\tau_M/	au_{M_0}$ | $2\pi^2 t^{-1/2} \left(\frac{1}{-A_0'}\right)$ | $4\pi^{3/2}t^{-1/2}\exp\left(\frac{h}{t}\right)$ | $4\pi t^{-1} h^{1/2}$ |
| l_M/l_{M_0} | $\left[\frac{2}{3}t\left(\frac{C_0}{-A_0'}\right)\right]^{1/2}$ | $t^{1/2}$ | $rac{\zeta(3/2)^{1/2}}{\pi^{1/4}} t^{1/4} h^{1/4}$ |

TABLE I. Expressions and leading order dependence of the relevant coefficients of magnon transport theory for $t \ll h$ and $t \gg h$. The coefficients are normalized as in Fig.1 and Fig.2.



FIG. 1. Thermo-magnetic coefficients computed from the magnon transport theory (low temperature approximation). The coefficients are normalized to: $\sigma_{M_0} = \tau_c m v_m^2 / \mu_0$, $\epsilon_{M_0} = -k_B / (2\mu_B)$, $\kappa_0 = nk_B \tau_c v_m^2$, $\tau_{M_0} = \tau_r / m$, $l_{M_0} = (\tau_c \tau_r)^{1/2} v_m$, $v_{M_0} = (\tau_c / \tau_r)^{1/2} m v_m$. For all graphs, the values of h are 10^{-5} , 10^{-4} and 10^{-3} (red, green and blue, respectively).

typical temperature $T_m = 480$ K and an effective mass $m^* = 2.5 \cdot 10^{-28}$ kg, which is about 280 times the electron mass (here we have used the relation $M_0 = \mu_B/a^3$ with $a \sim 0.36 \cdot 10^{-9}$ m being the typical distance between magnetic ions). The field H_0 , appearing in the ground state energy ϵ_H of Eq.(6), is the sum of the anisotropy field along one of the easy axis $\mu_0 H_{AN} \sim 0.017$ T⁴¹ and of the applied field H_a . For low applied fields, $H_a \ll H_{AN}$, we have $h \sim 0.5 \cdot 10^{-4}$, while for high applied fields, $H_a \gg H_{AN}$, we have $h = 10^{-3}$ at $\mu_0 H_a = 0.35$ T. The remaining parameters are $m = 6.8 \cdot 10^{-4}$ and



FIG. 2. Spin Seebeck effect for the magnon transport theory (low temperature approximation). j_{MS} is the magnetization current source normalized to $j_{MS_0} = -\epsilon_{M_0}\sigma_{M_0}\nabla T$. The main plot shows the temperature dependence at different fields. The inset shows the field dependence at different temperatures.

 $v_m = 6.6 \cdot 10^3 \text{ ms}^{-1}$. By assuming $\tau_r \approx \tau_c = 1$ ns, we obtain $j_{MS_0} / \nabla T = k_B \tau_c m v_m^2 / (2\mu_0 \mu_B) = 17.6 \text{ A s}^{-1} \text{ K}^{-1}$ m.

The previous values can be used to compute the order of magnitude of the spin Seebeck effect, by evaluating the magnetization current which is injected into the Pt layer by means of the properties of the inverse spin Hall effect in Pt. The injection of the magnetization current source into the metallic layer is due to the conversion of the magnetic moment of the magnons at the interface into a spin accumulation in Pt. The microscopic mechanisms involved 12-18 as well as the role played by imperfect interfaces⁴⁶ have been already analyzed in detail. From the point of view of the thermodynamic theory of Johnson and Silsbee³⁵ the passage of the magnetization current between two layers is described by solving the diffusion problem for the two materials and by imposing the appropriate boundary conditions²⁹. Each layer is characterized by a diffusion length for the magnetization current $l_M = (\mu_0 \sigma_M \tau_M)^{1/2}$ which is related to intrinsic



FIG. 3. Thermo-magnetic coefficients computed from the magnon transport theory (high temperature approximation). The coefficients are normalized to the same values reported in the caption of Fig.1. For all graphs, the values of h are 10^{-5} , 10^{-4} and 10^{-3} (red, green and blue, respectively).



FIG. 4. Spin Seebeck effect for the magnon transport theory (high temperature approximation). j_{MS} is the magnetization current source normalized as in Fig.2. Main plot and inset have the same meaning as in Fig.2.

properties of each material: the magnetization conductivity σ_M and the time constant τ_M . At the interface between the two layers, one requires the magnetization current density j_M to be continuous and the potentials H^* to be related by the interface resistance³⁵.

In the present paper we are interested in the evaluation of the order of magnitude of the spin Seebeck effect 8

that can be obtained in bulk YIG at low temperature. Using the inverse spin Hall effect of Pt, the magnetization current is converted into an electric voltage with a coefficient $1.3 \cdot 10^{-4}$ Vm⁻¹A⁻¹ s²⁹. Therefore we find that the spin Seebeck signal at T = 48 K (t = 0.104)is 3.7 μ V/K at low fields and it decreases to 2.9 μ V/K at 9 T (h = 0.025) in agreement with the measurements reported in Ref. [37] for a YIG slab of 1 mm of thickness and a thin Pt layer²⁹. In the theory, this effect is the consequence of the change of the Bose-Einstein distribution, Eq.(5), with the field dependent energy term ϵ_H , which is strongly pronounced for low q magnons. Similar conclusions have been achieved in Refs. [24], [47] and [48]. A detailed comparison with experimental data at several temperatures and fields requires also to take care of the current injection at the YIG/Pt interface, which will be the aim of future works. The agreement found at 48 K is obtained by using a transmission coefficient for the current at the YIG/Pt interface of 75% which is quite close to the value of 50% that was used at room temperature in Ref. [29].

VII. DISCUSSION AND CONCLUSIONS

We have used the Boltzmann transport theory in the relaxation time approximation to describe the thermal transport of spin waves in an insulating ferromagnet in the framework of the Johnson and Silsbee thermodynamic theory³⁵. Within this approach, the thermodynamic force associated with the magnetization current is the potential H^* which, in the case of magnon transport, is directly related to the magnon chemical potential, that is $\mu_m = 2\mu_0\mu_B H^*$. The kinetic coefficients of the constitutive thermo-magnetic transport equations are computed analytically by assuming an isotropic dispersion relation for magnons. The main outcome of the study is that the transport coefficients are analytical expressions containing the microscopic parameters of the material.

We have found several interesting properties in the magnetic field and temperature dependences of the kinetic coefficients. The absolute thermo-magnetic power coefficient ϵ_M , relating the gradient of the potential of the magnetization current and the gradient of the temperature, in the limit of low temperature and low field, is a constant $\epsilon_M = -0.6419 k_B/\mu_B$. In the limit of very low temperatures the spin Peltier coefficient Π_M , relating the heat and the magnetization currents, tends to a finite value which depends only on the amplitude of the magnetic field. This indicates the possibility to exploit the spin Peltier effect as an efficient cooling mechanism in cryogenics.

By inserting the typical values for YIG, one of the most studied spin Seebeck materials, we have computed the order of magnitude of the spin Seebeck experiments in bulk YIG. It is worth noting that while the theory is able to reproduce rather well the initial increase of the spin Seebeck effect as a function of temperature up to around 50 K, as reported in Ref. [37], the predictions above 50 K are much higher than the measured ones. This difference deserves special attention. Considering YIG, there are a certain number of important aspects that have been neglected here: the presence of different branches which are active above the 40 K region and the special dispersion relation of ferrimagnets⁴³. Another important point to mention is the fact that, as soon as the temperature is increased, the saturation magnetization M_s decreases significantly below the zero temperature value M_0 and this effect is not only caused by thermal spin waves. At intermediate temperatures the equilibrium magnetization $M_s(T)$ is mainly ascribed to localized magnetic fluctuations and the thermal spin waves, that can build up upon M_s , play only a minor role in determining the thermal content of the system. A theory taking into account the superposition of both local fluctuations and spin waves may be able to describe the details of the room temperature spin Seebeck effect. An interesting development along this line can be envisaged in considering an explicit dependence of the scattering time constant $\tau_c(q)$ on the magnon wavenumber q, as in Ref. [24] and [48]. Indeed, the analytical results of the present theory can be extended to the case of a $\tau_c(q)$ expressed as a power series in q. This can be the subject of a future development of the present work.

ACKNOWLEDGMENTS

This work has been carried out within the Joint Research Project EXL04 (SpinCal), funded by the European Metrology Research Programme. The EMRP is jointly funded by the EMRP participating countries within EURAMET and the European Union.

Appendix A: Calculation of coefficients

1. Definitions of the coefficients

The equilibrium and transport coefficients entering the theory are here defined as

$$A_r = \frac{(2\pi)^2 (k_B T_m)^{3/2}}{n (k_B T)^{r+3/2}} \frac{1}{(2\pi)^3} \int_{\Sigma} \epsilon^r g_0 d^3 q, \qquad (A1)$$

$$A'_{0} = (2\pi)^{2} \frac{(k_{B}T_{m})^{3/2}}{n(k_{B}T)^{1/2}} \frac{1}{(2\pi)^{3}} \int_{\Sigma} \frac{\partial g_{0}}{\partial \epsilon} d^{3}q, \qquad (A2)$$

and

$$C_r = -\frac{6\pi^2 (k_B T_m)^{3/2} m^*}{n (k_B T)^{3/2+r}} \frac{1}{(2\pi)^3} \int_{\Sigma} f_c(q) v_x^2 (\epsilon - \mu_m)^r \frac{\partial g_0}{\partial \epsilon} d^3 q$$
(A3)

where Σ is the first Brillouin zone of the reciprocal space, n is the density of elementary magnetic moments and

 $f_c(q)$ is the normalized wavenumber dependence of the collision time τ_c . For the calculation of the integrals, a standard method is adopted⁴⁴. Since all the coefficients in Eqs.(A1-A3) contain integrals $(2\pi)^{-3} \int d^3 q$ extending over Σ , their computation for a cubic lattice with lattice constant *a* gives rise to a factor $1/a^3$ which corresponds to the number of degrees-of-freedom per unit volume of the system. Then, the shape of Σ is replaced by a sphere Σ_0 in the *q* space of radius $q_0 = \pi/a_0$ giving rise to the same number of degrees-of-freedom. This corresponds to take $a_0 = (\pi/6)^{1/3}a$. This approximation is exact at low temperature for any lattice.

2. Low q approximation

At low temperature we take the low q approximation of the dispersion relation of Eq.(6). The group velocity is $\boldsymbol{v} = (2D/\hbar)\boldsymbol{q}$ and the energy of the state $q = q_0$ is $\epsilon_0 = \pi^2 D/a_0^2$. The integral over the Σ_0 sphere on the \boldsymbol{q} space is first performed over the spherical angles θ_q and φ_q giving a 4π factor. Then the integrals reduce to the form

$$\frac{1}{(2\pi)^3} \int_{\Sigma_0} d^3 q = \frac{n}{(2\pi)^2} \frac{1}{(k_B T_m)^{3/2}} \int (\epsilon - \epsilon_H)^{1/2} d\epsilon.$$
(A4)

The equilibrium coefficients A_r are calculated from Eq.(A1) and Eq.(A4) by changing the variable of integration to $y = (\epsilon - \epsilon_H)/(k_B T)$. We obtain

$$A_r = \int_0^{y_0} \frac{y^{1/2} (y + y_H)^r}{\exp(y + y_H) - 1} dy$$
 (A5)

where $y_H = \epsilon_H/(k_BT) = h/t$ and $y_0 = \epsilon_0/(k_BT)$. If the temperature is low, we can let the upper limit of the integral to go to infinity, $y_0 \to \infty$, and the obtained expression will be a function of y_H only. In particular

$$A_r = \sum_{i=0}^r \binom{r}{i} y_H^{r-i} I_{1/2+i}(y_H),$$
(A6)

where we have used the binomial coefficient $\binom{r}{i}$ and we have defined the integral

$$I_s(y_H) = \int_0^\infty \frac{y^s}{\exp(y + y_H) - 1} dy$$
 (A7)

which can be computed analytically (see Appendix B). For small y_H we have⁴⁹

$$I_s(y_H) = \Gamma(s+1) \operatorname{Li}_{s+1}(e^{-y_H})$$
(A8)

where $\Gamma(\cdot)$ is the gamma function and $\operatorname{Li}_n(z)$ is the polylogarithm function⁵⁰. As $\operatorname{Li}_n(1) = \zeta(n)$, where $\zeta(\cdot)$ is the Riemann zeta function, we have

$$I_s(0) = \Gamma(s+1)\zeta(s+1). \tag{A9}$$

For example, the coefficient for the number of magnons is $A_0 = I_{1/2}(y_H)$ and the coefficient for the average energy is $A_1 = I_{3/2}(y_H) + I_{1/2}(y_H)y_H$. For h = 0 and low q, we have $A_r(0) = \Gamma(3/2 + r)\zeta(3/2 + r)$.

In an analogous way we compute the coefficient A'_0 given by Eq.(A2). By making an integration by parts we find

$$A'_{0} = -\frac{1}{2}I_{-1/2}(y_{H}).$$
 (A10)

The coefficient for h = 0 is $A'_0(0) = -(1/2)\Gamma(1/2)\zeta(1/2)$.

Finally, the integral of Eq.(A3) is calculated by taking a constant collision time ($f_c(q) = 1$). After integration by parts we have

$$C_r = \int_0^{y_0} \frac{\partial \eta_r}{\partial y} g_0 dy \tag{A11}$$

with $\eta_r = y^{3/2} (y + y_H)^r$. By writing $\partial \eta_r / \partial y$ as

$$\frac{\partial \eta_r}{\partial y} = \frac{3}{2} y^{1/2} (y + y_H)^r + r y^{3/2} (y + y_H)^{r-1}, \quad (A12)$$

we obtain

$$\frac{\partial \eta_r}{\partial y} = \frac{3}{2} y^{1/2} \sum_{k=0}^r \binom{r}{k} y_H^{r-k} y^k + r y^{3/2} \sum_{k=0}^{r-1} \binom{r-1}{k} y_H^{r-1-k} y^k.$$
(A13)

By using the identity $\binom{r}{k} = \frac{r}{k} \binom{r-1}{k-1}$ we have

$$\frac{\partial \eta_r}{\partial y} = \sum_{k=0}^r \left(\frac{3}{2} + k\right) \, \binom{r}{k} y_H^{r-k} \, y^{1/2+k}. \tag{A14}$$

Now, by letting $y_0 \to \infty$ we obtain

$$C_r = \sum_{k=0}^r \left(\frac{3}{2} + k\right) {\binom{r}{k}} y_H^{r-k} I_{1/2+k}(y_H).$$
(A15)

For h = 0 we have $C_r(0) = (3/2 + r)\Gamma(3/2 + r)\zeta(3/2 + r)$.

3. High q isotropic approximation

At high temperature also the high wavenumbers of the spin waves are excited, so we assume an expression for the dispersion relation which is isotropic and reaches the maximum energy $\epsilon = \epsilon_m + \epsilon_H$ at $q = q_0$ (see Fig.5). An expression with this property is

$$\epsilon = \epsilon_m \sin^2(a_0 q/2) + \epsilon_H \tag{A16}$$

where $\epsilon_m = 4D/a_0^2$ and the modulus of the group velocity is $v = (2D)/(a_0\hbar) \sin(a_0q)$. The isotropic high q approximation would be in principle valid at any temperature, but we have to consider that the whole spin wave picture is based on the approximation of small deviations from the equilibrium state M_0 , so in practice it is reasonable to take $T = T_m$ (t = 1) as an upper limit. The integrals are performed by changing variable from the reciprocal space to the energy and then by using $x = (\epsilon - \epsilon_H)/\epsilon_m$. The integrals become

$$\frac{1}{(2\pi)^3} \int_{\Sigma_0} d^3 q = \frac{12n}{\pi^3} \int_0^1 \rho_m(x) dx$$
 (A17)

where $\rho_m(x) = [x(1-x)]^{-1/2} (\arcsin(x^{1/2}))^2$. Using x as a new integration variable, we have:

$$A_r = y_m^{3/2} \int_0^1 (y_m x + y_H)^r g_0 \rho_m(x) dx, \qquad (A18)$$

$$A_0' = y_m^{1/2} \int_0^1 \frac{\partial g_0}{\partial x} \rho_m(x) dx, \qquad (A19)$$

where $g_0 = (\exp(y_m x + y_H) - 1)^{-1}$ and $y_m = \epsilon_m/(k_B T) = 4(6/\pi)^{2/3}/t$, and for the transport coefficients, by using the same assumption of the low q case, we find

$$C_r = -y_m^{3/2} \int_0^1 x(1-x)(y_H + y_m x)^r \frac{\partial g_0}{\partial x} \rho_m(x) dx.$$
(A20)

The coefficients can be computed numerically and they can be represented as a function of the normalized temperature t and of the ratio h/t.



FIG. 5. Magnon dispersion relations. The dashed line is the low q approximation of Eq.(6). The full line is the high q isotropic approximation of Eq.(A16).

Appendix B: Expressions for $I_s(y_H)$

At low temperature the coefficients are all expressed in terms of the integral of Eq.(A7) which is a function of $y_H = h/t$. We can subdivide the behavior of $I_s(y_H)$ into: a) $y_H \ll 1$, i.e. $h \ll t$, which corresponds to the behavior at low fields and b) $y_H \gg 1$, i.e. $t \ll h$, which corresponds to the behavior at very low temperatures.

a. $y_H \ll 1$. At low y_H the integral can be expressed in terms of the polylogarithm function (Eq.(A8)). A power expansion of the polylogarithm for small x is⁴⁹

$$\operatorname{Li}_{n}(e^{x}) = \Gamma(1-n)(-x)^{n-1} + \sum_{k=0}^{\infty} \frac{\zeta(n-k)}{k!} x^{k}.$$
 (B1)

The expression for $I_s(y_H)$ of Eq.(A8) then becomes

- * Present address: Laboratorio MDM, IMM-CNR, Via Olivetti 2, 20864 Agrate Brianza (MB), Italy; elena.ferraro@mdm.imm.cnr.it
- ¹ K. Uchida, H. Adachi, T. Ota, H. Nakayama, S. Maekawa, and E. Saitoh, Appl. Phys. Lett. **97**, 172505 (2010).
- ² I. Zutic, J. Fabian, and S. D. Sarma, Rev. Mod. Phys. 76, 323 (2004).
- ³ G. E. W. Bauer, E. Saitoh, and B. J. van Wees, Nat. Mater. **11**, 391 (2012).
- ⁴ S. R. Boona, R. C. Myers, and J. P. Heremans, Energy Environ. Sci. 7, 885 (2014).
- ⁵ K. Uchida, J. Xiao, H. Adachi, J. Ohe, S. Takahashi, J. Ieda, T. Ota, Y. Kajiwara, H. Umezawa, H. Kawai, G. E. W. Bauer, S. Maekawa, and E. Saitoh, Nat. Mater. 9, 894 (2010).
- ⁶ K. Uchida, T. Ota, H. Adachi, J. Xiao, T. Nonaka, Y. Kajiwara, G. E. W. Bauer, S. Maekawa, and E. Saitoh, J. Appl. Phys. **111**, 103903 (2012).
- ⁷ K. Uchida, T. Nonaka, T. Kikkawa, Y. Kajiwara, and E. Saitoh, Phys. Rev. B 87, 104412 (2013).
- ⁸ T. Kikkawa, K. Uchida, Y. Shiomi, Z. Qiu, D. Hou, D. Tian, H. Nakayama, X.-F. Jin, and E. Saitoh, Phys. Rev. Lett. **110**, 067207 (2013).
- ⁹ B. F. Miao, S. Y. Huang, D. Qu, and C. L. Chien, Phys. Rev. B **111**, 066602 (2013).
- ¹⁰ H. Adachi, K. Uchida, E. Saitoh, and S. Maekawa, Rep. Prog. Phys. **76**, 036501 (2013).
- ¹¹ G. Siegel, M. C. Prestgard, S. Teng, and A. Tiwari, Sci. Rep. 4, 4429 (2014).
- ¹² A. Brataas, Y. V. Nazarov, and G. E. W. Bauer, Phys. Rev. Lett. 84, 2481 (2000).
- ¹³ J. ichiro Ohe, H. Adachi, S. Takahashi, and S. Maekawa, Phys. Rev. B 83, 115118 (2011).
- ¹⁴ Z. Qiu, K. Ando, K. Uchida, Y. Kajiwara, R. Takahashi, H. Nakayama, T. An, Y. Fujikawa, and E. Saitoh, Appl. Phys. Lett. **103**, 092404 (2013).
- ¹⁵ S. Hoffman, K. Sato, and Y. Tserkovnyak, Phys. Rev. B 88, 064408 (2013).
- ¹⁶ E. G. Tveten, A. Brataas, and Y. Tserkovnyak, Phys. Rev.

$$I_{s}(y_{H}) = \Gamma(s+1) \left[\Gamma(-s)y_{H}^{s} + \sum_{k=0}^{\infty} (-1)^{k} \frac{\zeta(s+1-k)}{k!} y_{H}^{k} \right]$$
(B2)

where the power series can be computed up to the desired order. Table I reports the expression of the relevant parameters for magnon transport theory by taking the leading order in h/t only, while the curves reported in the figures are computed by using Eq.(B2) up to the order k = 9.

b. $y_H \gg 1$. In the limit $y_H \to \infty$ the expression of Eq.(A7) is

$$I_s(y_H) = \Gamma(s+1) \exp(-y_H). \tag{B3}$$

This means that in the $T \to 0$ limit with $H_0 \neq 0$ all the integrals I_s decay exponentially to zero.

B 92, 180412 (2015).

- ¹⁷ L. Chotorlishvili, Z. Toklikishvili, S. Etesami, V. Dugaev, J. Barna, and J. Berakdar, J. Magn. Magn. Mater. **396**, 254 (2015).
- ¹⁸ S. A. Bender and Y. Tserkovnyak, Phys. Rev. B **91**, 140402(R) (2015).
- ¹⁹ J. Xiao, G. E. W. Bauer, K.-c. Uchida, E. Saitoh, and S. Maekawa, Phys. Rev. B **81**, 214418 (2010).
- ²⁰ J. Xiao, G. E. W. Bauer, K.-c. Uchida, E. Saitoh, and S. Maekawa, Phys. Rev. B 82, 099904 (2010).
- ²¹ M. Schreier, A. Kamra, M. Weiler, J. Xiao, G. E. W. Bauer, R. Gross, and S. T. B. Goennenwein, Phys. Rev. B 88, 094410 (2013).
- ²² S. S.-L. Zhang and S. Zhang, Phys. Rev. Lett. **109**, 096603 (2012).
- ²³ S. S.-L. Zhang and S. Zhang, Phys. Rev. B 86, 214424 (2012).
- ²⁴ S. M. Rezende, R. L. Rodríguez-Suárez, R. O. Cunha, A. R. Rodrigues, F. L. A. Machado, G. A. Fonseca Guerra, J. C. Lopez Ortiz, and A. Azevedo, Phys. Rev. B 89, 014416 (2014).
- ²⁵ S. M. Rezende, R. L. Rodríguez-Suárez, J. C. Lopez Ortiz, and A. Azevedo, Phys. Rev. B 89, 134406 (2014).
- ²⁶ H. Jin, S. R. Boona, Z. Yang, R. C. Myers, and J. P. Heremans, Phys. Rev. B **92**, 054436 (2015).
- ²⁷ K. Nakata, P. Simon, and D. Loss, Phys. Rev. B **92**, 134425 (2015).
- ²⁸ S. M. Rezende, R. L. Rodríguez-Suárez, R. O. Cunha, J. C. López Ortiz, and A. Azevedo, J. Magn. Magn. Mater. **400**, 171 (2016).
- ²⁹ V. Basso, E. Ferraro, A. Sola, A. Magni, M. Kuepferling, and M. Pasquale, Phys. Rev. B **93**, 184421 (2016).
- ³⁰ E. Anderson, Phys. Rev. **134**, A1581 (1964).
- ³¹ D. J. Sanders and D. Walton, Phys. Rev. B **15**, 1489 (1977).
- ³² A. Kehlberger, U. Ritzmann, D. Hinzke, E. Guo, J. Cramer, G. Jakob, M. C. Onbasli, D. H. Kim, C. A. Ross, M. B. Jungfleish, B. Hillebrands, U. Nowak, and M. Kläui, Phys. Rev. Lett. **115**, 096602 (2015).

- ³³ M. Agrawal, V. I. Vasyuchka, A. A. Serga, A. D. Karenowska, G. A. Melkov, and B. Hillebrands, Phys. Rev. Lett. **111**, 107204 (2013).
- ³⁴ B. Liao, J. Zhou, and G. Chen, Phys. Rev. Lett. **113**, 025902 (2014).
- ³⁵ M. Johnson and R. H. Silsbee, Phys. Rev. B **35**, 4959 (1987).
- ³⁶ L. J. Cornelissen, K. J. H. Peters, G. E. W. Bauer, R. A. Duine, and B. J. van Wees, Phys. Rev. B **94**, 014412 (2016).
- ³⁷ T. Kikkawa, K.-i. Uchida, S. Daimon, Z. Qiu, Y. Shiomi, and E. Saitoh, Phys. Rev. B **92**, 064413 (2015).
- ³⁸ H. B. Callen, *Thermodynamics and an introduction to ther*mostatistics (John Wiley and Sons, New York, 1985).
- ³⁹ J. Sólyom, Fundamentals of the Physics of Solids (Springer, Berlin, 2007).
- ⁴⁰ A. G. Gurevich and G. A. Melkov, *Magnetization oscilla*-

tions and waves (CRC Press, Boca Raton, 1996).

- ⁴¹ D. D. Stancil and A. Prabhakar, Spin Waves. Theory and Applications (Springer, New York, 2009).
- ⁴² C. Kittel, Introduction to solid state physics, 8th edition (John Wiley and Sons, New York, 2005).
- ⁴³ V. Cherepanov, I. Kolokolov, and V. Lvov, Phys. Rep. 229, 81 (1993).
- ⁴⁴ A. H. Wilson, *Theory of metals* (Cambridge University Press, Cambridge, 1953).
- ⁴⁵ R. L. Douglass, Phys. Rev. **129**, 1132 (1963).
- ⁴⁶ Z. Qiu, D. Hou, K. Uchida, and E. Saitoh, J. Phys. D: Appl. Phys. 48, 164013 (2015).
- ⁴⁷ U. Ritzmann, D. Hinzke, A. Kehlberger, E.-J. Guo, M. Kläui, and U. Nowak, Phys. Rev. B **92**, 174411 (2015).
- ⁴⁸ I. Diniz and A. T. Costa, New J. Phys. **18**, 052002 (2016).
- ⁴⁹ J. E. Robinson, Phys. Rev. **83**, 678 (1951).
- ⁵⁰ L. Lewin, *Polylogarithms and associated fucntions* (North-Holland, New York, 1981).